




Accelerated Light Fading Test Results

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

Sample # AaI_20071212_SN001

260 Megalux-hours completed

Conservation Display Rating *	
Lower Exposure Limit (Megalux hours)	Upper Exposure limit (Megalux hours)
37	80

* Please read document **AaI_2009_0118_TA-01.pdf**, "An Overview of the AaI&A Conservation Display Ratings", located on the Documents page of the AaI&A website for an explanation of the conservation display ratings.

Document #: AaI_20071212_SN001Lf.pdf Rev: October 3, 2012

Test Print Prepared by: Aardenburg Imaging & Archives

Copyright 2012. This report has been prepared for the exclusive use of members of Aardenburg Imaging & Archives. Members may share this information with other members, friends, colleagues, and individual clients. It may also be distributed to groups for educational purposes (classes, lectures, educational seminars. etc). However, all contents including but not limited to Conservation Display Ratings may not be posted to web sites and may not be reproduced or distributed for corporate research, marketing, or other promotional purposes without written permission from Aardenburg Imaging & Archives.

For more information please contact: info@aardenburg-imaging.com



About this Report

This report contains light fastness information about a single test print produced by a specific digital printing system. “System” refers to all hardware, software, and materials used to make the finished print. The hardware, software, material components, and printmaker’s skills contribute to the final image quality and image permanence. The tested sample is made with current or recently discontinued stocks of commercially available products unless otherwise stated. Each sample has been prepared by Aardenburg Imaging & Archives or one of its members in accordance with customary print making practices unless otherwise noted. The sample may also contain additional finishing materials such as overcoats and laminates which are also noted when used. Finally, the sample has been tested under standardized conditions that are defined on the Sample Description page (see page 2). AaI&A makes every effort to ensure but cannot guarantee that the samples are properly identified and documented and that test results are accurate. For this reason, AaI&A also strives to test independently produced sample replicates in order to increase sampling confidence and to provide information on process variability. Please compare the results in this report to replicate test samples when the data become available.

Understanding the Test Results



AaI_StandardColorSet(v2)forSRGB.tif

The magnitude and visual appearance of fading depends not only on the chosen printing system but the chosen image as well. In other words, different images are comprised of different colors, and the fading relationships between those colors dictate how the image will look as it fades. The sample print in this test report was made by reproducing the digital image shown on the left. It contains 30 standard colors. 24 of the colors are colorimetrically matched to the Macbeth ColorChecker™ chart viewed under D50 illumination. The remaining six colors supplement the ColorChecker™ array with four additional skin tone colors, one patch for paper white, and another for maximum black. The additional colors also round out the distribution of L* lightness values in the test target.

Information about the fading characteristics of the product is provided in three ways:

1) ***You can visually assess the fading.*** The target images reproduced in this report are digitally reconstructed from the spectrally measured color data rather than scanning or otherwise reproducing the physical print by conventional techniques. This method ensures a colorimetrically accurate representation of the print appearance as the print fades. A calibrated monitor is recommended to experience the best possible reproduction of the test sample appearance. The side-by-side presentation of the target images simulates looking at the light-exposed print along side a perfect duplicate of the unexposed original print. The “Before/After” Layer mode takes advantage of Adobe Reader Layer technology. Toggle the “Before/After” layer on and off using the layers feature of Adobe Reader to directly switch between the light exposed print colors and the initial print colors for the image located on the right side of each page. Also, use Adobe Reader’s full screen mode to cycle through the pages and “animate” the fading.

2) ***I* Color and tonal accuracy scores are reported.*** This report includes I* metric scores that compare the color and tonal relationships of the light exposed samples to the color and tonal relationships existing in the original print prior to light exposure. Perfect I* scores of 100% can be approached when no significant fading occurs. Average scores above 90% generally indicate excellent retention of original quality, 80% good, 70% fair, etc., but your conclusions may vary depending on your image quality requirements. ***I* color*** rates the retained color accuracy (hue and chroma) while ***I* tone*** rates the retained tonal accuracy (lightness and contrast). The score is on a percentile scale where 100% is a perfect match between the comparison image (e.g., “after” light exposure) and the reference image (e.g., “before” any light exposure). 0% ***I* color*** means no color accuracy is left. 0% ***I* tone*** means essentially no tonality remains and all image information content is lost. Negative I* values have significance as well and contribute to the average I* score when they occur. Negative I* color values mean false color has occurred, for example, when a skin tone turns green or a neutral gray becomes distinctly colorful. Negative I* tone scores mean visual contrast between colors has become inverted (i.e., like the tonal relationships in a photographic film negative). Serious image quality problems must arise before false colors and/or tones appear. For more information on the I* metric, please refer to the AaI&A web site.

3) ***Color changes are also reported using the classic color difference model, ΔE .*** Note that ΔE values lose perceptual scaling significance when they become large (e.g., > 15). Also, the ΔE equation does not unambiguously measure changes in image contrast. This limitation is generally not a problem for paints and textiles, but can be a serious oversight when evaluating photographic images. It was a major reason behind the development of the I* metric.



Sample Description


Printer: Canon iPF5000

Ink: Canon Lucia OEM

Paper: Epson Exhibition Fiber 325gsm

Sample #: AaI_20071212_SN001

Test Print Prepared by: AaI&A



AaI_StandardColorSet(v2)forSRGB.tif

Test Image: AaI_StandardColorSet(v2)forSRGB.tif

RIP/Driver settings: Canon 16bit plug-in for PS, highest quality driver settings

Media Setting: "Special 5"

Printed: December 12, 2007

Original print colors measured on: January 08, 2008

Test started on: January 10, 2008

Profile: AaI_iPF5000_EpExhiFiber(1a).icc

Rendering Intent: Perceptual

Profile type: custom

Profile Creation Software: Gretag/Macbeth Profilemaker 5.0.8

Paper White Color (UV–included versus UV–excluded) and Maximum Printed Black						
Optical Brighteners present? yes	L*		a*		b*	
	UV inc	UV exc	UV inc	UV exc	UV inc	UV exc
Maximum Paper White (no colorants printed)	96.2	96.1	1.3	−0.4	−4.9	1.3
(1) ΔL*, Δa*, Δb* respectively	0.1		1.7		6.2	
(1) Calculated differences, especially for Δb*, indicate the role and magnitude of fluorescence on original paper color						
Maximum Printed black (UV included)	L* = 6.1		a* = 0.4		b* = −1.5	

Light Source: Phillips Colortone F40T12/C50

Filter/Glazing: Sample framed under Glass*

Light Exposure Cycle: 8 hours on, 4 hours off, twice per 24 hours

Average Illuminance during "on" cycle: 11,725 Lux

Average Temperature: 23.2°C over full test duration, 24.6°C during light exposure

Average Relative humidity: 58.5% RH full test period, 59.1% RH during light exposure

CIELAB measurements: D50 2° observer, Xrite Gretag/Macbeth Spectrolino/Spectroscan

Replicates/Compare to:


No Replicates are available at this time.

Notes/Comments:


* The Phillips Colortone F40T12/C50 fluorescent light source and ordinary glass picture frame glazing yields UVA content and overall spectral power similar to natural 5000°K daylight entering a window and then striking a print that has been framed by **standard acrylic glazing** rather than ordinary glass. Other light sources and/or different glazing options may yield greater or lesser fade rates (generally, a 2-5x increase in fade rate for direct sunlight compared to UV-excluded sources at the same Lux level). The spectral quality of the light can also affect individual colors differently.

Table to Convert Megalux-hours of Light Exposure to estimated “Years on Display”												
Indoor Light Levels for Print Display		Multiply Mlux-hrs by	Megalux-hours in test									
Light Exposure	Description		10	20	30	40	50	60	70	80	90	100
≤ 10 Lux 24 hours per day	Interior rooms, storage areas, or hallways without windows, illuminated sparingly by artificial lighting	11.42	114	228	342	457	571	685	799	913	1027	1142
50 Lux 12 hours per day	“Museum Standard” display condition	4.57	46	91	137	183	228	274	325	365	411	457
120 Lux 12 hours per day “Kodak Display Years” (1)	Average home illumination level for photos is ~ 60 lux. 90% of all displayed photos do not exceed 120 lux (1).	1.90	19	38	57	76	95	114	133	152	171	190
228 Lux 12 hours per day	Relatively bright home or office. Note the simple 1:1 relationship between “years on display” and Mlux-hr values at this condition.	1.00	10	20	30	40	50	60	70	80	90	100
450 Lux 12 hours per day “WIR Display Years” (2) Also equals 500 lux for 11.8 hours per day	A bright home or commercial office building illumination level is 200-500 lux. Also, good illumination for color critical viewing and color matching tasks begins at about 500 lux.	0.51	5	10	15	20	25	30	35	41	46	51
2000 Lux 12 hours per day	Commercial Gallery. Also, critical color evaluation standards call for 2000 lux and a D50 illumination source.	0.114	1.1	2.3	3.4	4.6	5.7	6.8	8.0	9.1	10.3	11.4
5000 Lux 12 hours per day	E.g., Sunlight through a window striking print at an angle.	0.046	0.5	0.9	1.4	1.8	2.3	2.7	3.2	3.7	4.1	4.6
10,000 Lux 12 hours per day	South-facing window in U.S.A. , e.g., storefront display with photos directly facing window.	0.023	0.2	0.5	0.7	0.9	1.1	1.4	1.6	1.8	2.1	2.3
Light levels commonly encountered in the real world fluctuate widely throughout indoor print display environments and produce large variations in how long it takes for artwork to acquire light-induced damage. Use this table as a guide to estimate how many “years on display” (denoted in red text) it takes to accumulate the light exposure test dosage. Review the test results to decide which Megalux-hour dose has caused fading to your level of concern (e.g., just noticeable, easily noticeable, objectionable, etc.). Then choose the print display description that best represents how your print is likely to be displayed. You may want to obtain a lux meter and make some measurements in your own display environment! Note that as the years of display time increase, light-induced fading can be eclipsed by other serious aging mechanisms such as fading and/or staining caused by heat, humidity, and air pollutants. Mould damage can also occur at high humidity. Even when colorants remain water fast, direct contact with liquids may result in physical deformation and staining of the substrate. Also, temperature and especially humidity cycling can cause physical cracks and/or flaking, etc. Handling damage such as scratching, abrasion, tears and creases, and catastrophic damage by smoke, fire, flood, etc., also degrade print quality over time. Thus, as illumination levels are reduced other forms of degradation take on greater proportion of risk and may appear in shorter time intervals. (1) Eastman Kodak has cited this exposure condition and 90% confidence limit as a rationale for estimating print fading times of traditional color photo materials in typical home display environments. For recent light fading claims regarding its line of pigment-based inkjet printers, Kodak has adopted the higher level of 450lux/12 hours per day which is also used by Wilhelm Imaging Research, Inc. (See below). (2) Wilhelm Imaging Research (WIR) has standardized its light fastness ratings on 450 lux for 12 hours per day in order to estimate the years on display necessary to reach “noticeable” fading. This average light exposure condition, an assumed 75°F/60%RH temperature and humidity level, and WIR’s visually weighted densitometric endpoint criteria set V3.0 has become a de facto industry standard for most predictive light fading estimates in the absence of a published International Standards Organization (ISO) test standard.												

100_{color}/100_{tone}



Original Print Colors
(measured before light exposure)




Colors at **Zero Megalux-hours** of Light Exposure
(same as original print colors)

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*


Original Print Colors as Measured and at Start of Test

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	100	0.0	36.5		13.2		10.5	
B1	light Skin	100	0.0	65.1		14.7		12.6	
C1	blue sky	100	0.0	51.5		-4.1		-23.0	
D1	foliage	100	0.0	43.1		-12.5		27.1	
E1	blue flower	100	0.0	55.2		10.3		-27.0	
F1	bluish green	100	0.0	69.7		-30.2		-1.4	
A2	orange	100	0.0	61.4		33.9		59.9	
B2	purplish blue	100	0.0	37.7		12.1		-49.5	
C2	moderate red	100	0.0	46.1		49.2		14.1	
D2	purple	100	0.0	28.3		23.9		-25.0	
E2	yellow green	100	0.0	71.3		-22.5		62.2	
F2	orange yellow	100	0.0	71.1		16.2		70.3	
A3	blue	100	0.0	24.2		16.0		-55.5	
B3	green	100	0.0	54.5		-38.7		32.5	
C3	red	100	0.0	36.7		54.4		25.3	
D3	yellow	100	0.0	78.9		6.0		88.7	
E3	magenta	100	0.0	50.0		50.5		-19.6	
F3	cyan	100	0.0	51.3		-23.0		-30.3	
A4	white	100	0.0	93.1		1.8		-3.5	
B4	neutral 8	100	0.0	78.9		1.3		-3.5	
C4	neutral 6.5	100	0.0	65.4		1.2		-4.8	
D4	neutral 5	100	0.0	49.8		1.3		-3.2	
E4	neutral 3.5	100	0.0	36.6		1.1		-2.9	
F4	black	100	0.0	21.8		1.0		-1.5	
A5	paper white	100	0.0	96.1		1.5		-5.1	
B5	skin highlight L*=89	100	0.0	85.7		11.6		6.3	
C5	skin highlight L*=75	100	0.0	74.6		17.7		11.6	
D5	skin shadow L*=25	100	0.0	25.3		16.9		14.4	
E5	skin shadow L*=11	100	0.0	15.8		16.9		10.5	
F5	Max Black	100	0.0	6.1		0.4		-1.5	
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		100	100	0.0					
Average Score for the Worst 10% (3 lowest scoring patches)		100	100	0.0					

99.6_{color} / 98.4_{tone}




Original Print Colors
(measured before light exposure)




Colors after 10 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*


10 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	100.0	0.8	36.5	37.2	13.2	12.7	10.5	10.6
B1	light Skin	99.7	0.7	65.1	65.5	14.7	14.2	12.6	12.6
C1	blue sky	100.0	0.7	51.5	52.2	-4.1	-4.4	-23.0	-22.8
D1	foliage	100.0	0.6	43.1	43.6	-12.5	-12.8	27.1	27.2
E1	blue flower	99.7	0.9	55.2	55.8	10.3	9.8	-27.0	-26.7
F1	bluish green	100.0	0.6	69.7	70.0	-30.2	-30.1	-1.4	-1.9
A2	orange	99.6	0.9	61.4	61.9	33.9	33.1	59.9	60.1
B2	purplish blue	100.0	0.7	37.7	38.2	12.1	11.6	-49.5	-49.6
C2	moderate red	99.5	0.9	46.1	46.7	49.2	48.5	14.1	13.9
D2	purple	100.0	0.6	28.3	28.8	23.9	23.7	-25.0	-25.4
E2	yellow green	100.0	0.4	71.3	71.5	-22.5	-22.3	62.2	62.5
F2	orange yellow	99.9	0.6	71.1	71.4	16.2	15.7	70.3	70.5
A3	blue	100.0	0.6	24.2	24.7	16.0	15.7	-55.5	-55.6
B3	green	100.0	0.7	54.5	55.1	-38.7	-38.5	32.5	32.5
C3	red	100.0	0.4	36.7	37.0	54.4	54.2	25.3	25.1
D3	yellow	100.0	0.4	78.9	79.3	6.0	5.8	88.7	88.9
E3	magenta	99.5	1.0	50.0	50.6	50.5	49.7	-19.6	-19.4
F3	cyan	100.0	0.6	51.3	51.8	-23.0	-23.3	-30.3	-30.3
A4	white	99.2	0.6	93.1	93.3	1.8	1.5	-3.5	-3.0
B4	neutral 8	100.0	0.4	78.9	79.1	1.3	1.0	-3.5	-3.3
C4	neutral 6.5	100.0	0.7	65.4	65.9	1.2	0.8	-4.8	-4.6
D4	neutral 5	100.0	0.7	49.8	50.4	1.3	1.0	-3.2	-3.2
E4	neutral 3.5	100.0	0.6	36.6	37.1	1.1	0.9	-2.9	-3.0
F4	black	100.0	0.6	21.8	22.4	1.0	0.9	-1.5	-1.7
A5	paper white	96.6	0.8	96.1	96.1	1.5	1.3	-5.1	-4.3
B5	skin highlight L*=89	96.6	0.9	85.7	85.7	11.6	11.0	6.3	7.1
C5	skin highlight L*=75	98.8	0.8	74.6	74.8	17.7	17.1	11.6	12.0
D5	skin shadow L*=25	100.0	0.6	25.3	25.8	16.9	16.7	14.4	14.5
E5	skin shadow L*=11	99.4	0.6	15.8	16.0	16.9	17.0	10.5	11.1
F5	Max Black	100.0	0.1	6.1	6.1	0.4	0.5	-1.5	-1.7
Summary Results		I*Color	I*tone	 AARDENBURG IMAGING & ARCHIVES					
Average Score for all patches		99.6	98.4						
Average Score for the Worst 10% (3 lowest scoring patches)		97.3	97.0						

98.2_{color} / 97.7_{tone}



Original Print Colors
(measured before light exposure)



Colors after 20 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

20 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	98.7	1.2	36.5	37.5	13.2	12.5	10.5	10.5
B1	light Skin	98.3	1.1	65.1	65.8	14.7	13.9	12.6	12.6
C1	blue sky	98.7	1.2	51.5	52.4	-4.1	-4.6	-23.0	-22.4
D1	foliage	100.0	1.0	43.1	44.0	-12.5	-12.8	27.1	27.2
E1	blue flower	97.6	1.5	55.2	56.1	10.3	9.5	-27.0	-26.2
F1	bluish green	99.9	0.7	69.7	70.2	-30.2	-30.1	-1.4	-2.0
A2	orange	99.0	1.4	61.4	62.1	33.9	32.7	59.9	60.1
B2	purplish blue	98.5	1.5	37.7	38.5	12.1	10.9	-49.5	-49.0
C2	moderate red	98.7	1.4	46.1	46.9	49.2	48.1	14.1	13.7
D2	purple	100.0	0.9	28.3	29.1	23.9	23.5	-25.0	-25.2
E2	yellow green	100.0	0.5	71.3	71.7	-22.5	-22.4	62.2	62.5
F2	orange yellow	99.4	1.1	71.1	71.6	16.2	15.4	70.3	70.7
A3	blue	99.4	1.1	24.2	24.9	16.0	15.2	-55.5	-55.3
B3	green	100.0	1.1	54.5	55.5	-38.7	-38.4	32.5	32.0
C3	red	100.0	0.7	36.7	37.2	54.4	54.2	25.3	24.9
D3	yellow	99.6	1.0	78.9	79.3	6.0	5.7	88.7	89.5
E3	magenta	98.5	1.5	50.0	50.7	50.5	49.3	-19.6	-19.0
F3	cyan	99.9	1.0	51.3	52.1	-23.0	-23.5	-30.3	-30.0
A4	white	91.3	1.4	93.1	93.4	1.8	1.4	-3.5	-2.3
B4	neutral 8	96.2	1.0	78.9	79.3	1.3	0.9	-3.5	-2.8
C4	neutral 6.5	96.7	1.1	65.4	66.1	1.2	0.6	-4.8	-4.2
D4	neutral 5	100.0	1.1	49.8	50.7	1.3	0.8	-3.2	-3.1
E4	neutral 3.5	100.0	0.9	36.6	37.4	1.1	0.8	-2.9	-2.9
F4	black	100.0	0.9	21.8	22.7	1.0	0.8	-1.5	-1.7
A5	paper white	86.6	1.8	96.1	96.1	1.5	1.1	-5.1	-3.4
B5	skin highlight L*=89	93.3	1.4	85.7	85.9	11.6	10.8	6.3	7.4
C5	skin highlight L*=75	97.1	1.2	74.6	75.0	17.7	16.8	11.6	12.1
D5	skin shadow L*=25	99.8	1.0	25.3	26.1	16.9	16.4	14.4	14.5
E5	skin shadow L*=11	98.9	0.8	15.8	16.2	16.9	17.0	10.5	11.3
F5	Max Black	100.0	0.2	6.1	6.3	0.4	0.5	-1.5	-1.6

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

98.2

97.7


1.1

Average Score for the Worst 10%
(3 lowest scoring patches)

90.4


95.9

1.6




AARDENBURG IMAGING
& ARCHIVES

96.5_{color} / 97.1_{tone}




Original Print Colors
(measured before light exposure)




Colors after 30 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*


30 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	96.8	1.6	36.5	37.8	13.2	12.1	10.5	10.3
B1	light Skin	97.1	1.4	65.1	66.0	14.7	13.7	12.6	12.5
C1	blue sky	97.2	1.6	51.5	52.6	-4.1	-4.8	-23.0	-22.1
D1	foliage	100.0	1.3	43.1	44.3	-12.5	-12.9	27.1	26.9
E1	blue flower	95.7	2.0	55.2	56.2	10.3	9.2	-27.0	-25.7
F1	bluish green	98.7	1.1	69.7	70.4	-30.2	-30.0	-1.4	-2.3
A2	orange	98.4	1.9	61.4	62.3	33.9	32.3	59.9	60.1
B2	purplish blue	97.7	1.9	37.7	38.6	12.1	10.7	-49.5	-48.7
C2	moderate red	97.8	1.9	46.1	47.1	49.2	47.7	14.1	13.4
D2	purple	99.7	1.1	28.3	29.2	23.9	23.3	-25.0	-25.1
E2	yellow green	100.0	0.7	71.3	71.9	-22.5	-22.5	62.2	62.5
F2	orange yellow	98.9	1.5	71.1	71.8	16.2	15.1	70.3	70.9
A3	blue	98.7	1.5	24.2	25.0	16.0	14.8	-55.5	-55.1
B3	green	98.8	1.8	54.5	55.9	-38.7	-38.3	32.5	31.4
C3	red	99.5	1.0	36.7	37.3	54.4	54.0	25.3	24.6
D3	yellow	99.0	1.5	78.9	79.4	6.0	5.6	88.7	90.0
E3	magenta	97.6	1.9	50.0	50.8	50.5	49.0	-19.6	-18.7
F3	cyan	99.1	1.3	51.3	52.2	-23.0	-23.6	-30.3	-29.7
A4	white	84.9	2.0	93.1	93.4	1.8	1.2	-3.5	-1.7
B4	neutral 8	91.4	1.4	78.9	79.4	1.3	0.8	-3.5	-2.3
C4	neutral 6.5	93.4	1.4	65.4	66.3	1.2	0.4	-4.8	-4.0
D4	neutral 5	98.2	1.4	49.8	51.0	1.3	0.7	-3.2	-3.0
E4	neutral 3.5	100.0	1.2	36.6	37.6	1.1	0.7	-2.9	-2.8
F4	black	100.0	1.1	21.8	22.8	1.0	0.6	-1.5	-1.7
A5	paper white	77.4	2.6	96.1	96.1	1.5	0.9	-5.1	-2.5
B5	skin highlight L*=89	89.7	1.9	85.7	85.9	11.6	10.5	6.3	7.8
C5	skin highlight L*=75	95.9	1.5	74.6	75.2	17.7	16.5	11.6	12.2
D5	skin shadow L*=25	98.4	1.3	25.3	26.3	16.9	16.1	14.4	14.5
E5	skin shadow L*=11	96.4	1.3	15.8	16.3	16.9	17.0	10.5	11.8
F5	Max Black	100.0	0.2	6.1	6.3	0.4	0.5	-1.5	-1.4
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		96.5	97.1	1.5					
Average Score for the Worst 10% (3 lowest scoring patches)		84.0	94.8	2.2					

95.0_{color} / 96.7_{tone}



Original Print Colors
(measured before light exposure)



Colors after 40 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

40 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	94.9	1.9	36.5	37.9	13.2	11.8	10.5	10.4
B1	light Skin	96.1	1.7	65.1	66.2	14.7	13.5	12.6	12.4
C1	blue sky	95.6	1.9	51.5	52.7	-4.1	-5.1	-23.0	-21.8
D1	foliage	98.7	1.6	43.1	44.5	-12.5	-13.1	27.1	26.5
E1	blue flower	94.0	2.5	55.2	56.3	10.3	9.0	-27.0	-25.3
F1	bluish green	97.3	1.5	69.7	70.4	-30.2	-30.0	-1.4	-2.7
A2	orange	97.8	2.3	61.4	62.5	33.9	31.8	59.9	59.7
B2	purplish blue	97.4	2.0	37.7	38.5	12.1	10.5	-49.5	-48.6
C2	moderate red	96.9	2.3	46.1	47.2	49.2	47.5	14.1	13.0
D2	purple	98.9	1.3	28.3	29.3	23.9	23.0	-25.0	-25.0
E2	yellow green	100.0	0.7	71.3	72.0	-22.5	-22.6	62.2	62.2
F2	orange yellow	98.6	1.7	71.1	71.8	16.2	14.8	70.3	70.8
A3	blue	97.8	1.9	24.2	25.0	16.0	14.4	-55.5	-54.8
B3	green	96.8	2.7	54.5	56.1	-38.7	-38.1	32.5	30.4
C3	red	98.4	1.6	36.7	37.3	54.4	53.8	25.3	24.0
D3	yellow	98.8	1.6	78.9	79.4	6.0	5.4	88.7	90.1
E3	magenta	97.0	2.2	50.0	50.8	50.5	48.7	-19.6	-18.6
F3	cyan	98.1	1.5	51.3	52.2	-23.0	-23.8	-30.3	-29.4
A4	white	78.8	2.5	93.1	93.4	1.8	1.1	-3.5	-1.1
B4	neutral 8	87.5	1.8	78.9	79.4	1.3	0.7	-3.5	-2.0
C4	neutral 6.5	90.4	1.6	65.4	66.2	1.2	0.3	-4.8	-3.7
D4	neutral 5	96.2	1.5	49.8	51.0	1.3	0.5	-3.2	-2.8
E4	neutral 3.5	99.1	1.3	36.6	37.7	1.1	0.5	-2.9	-2.8
F4	black	99.7	1.2	21.8	22.9	1.0	0.5	-1.5	-1.7
A5	paper white	69.0	3.4	96.1	95.9	1.5	0.7	-5.1	-1.8
B5	skin highlight L*=89	89.2	1.9	85.7	85.9	11.6	10.5	6.3	7.9
C5	skin highlight L*=75	95.4	1.6	74.6	75.1	17.7	16.3	11.6	12.1
D5	skin shadow L*=25	96.6	1.7	25.3	26.4	16.9	15.7	14.4	14.2
E5	skin shadow L*=11	95.7	1.4	15.8	16.3	16.9	16.8	10.5	11.9
F5	Max Black	100.0	0.1	6.1	6.2	0.4	0.5	-1.5	-1.4

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

95.0

96.7


1.8

Average Score for the Worst 10%
(3 lowest scoring patches)

78.5


93.3

2.9




AARDENBURG IMAGING
& ARCHIVES

93.5_{color} / 96.0_{tone}



Original Print Colors
(measured before light exposure)



Colors after 50 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

50 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	93.3	2.3	36.5	38.2	13.2	11.7	10.5	9.8
B1	light Skin	95.2	1.9	65.1	66.4	14.7	13.4	12.6	12.0
C1	blue sky	94.6	2.2	51.5	52.9	-4.1	-5.2	-23.0	-21.6
D1	foliage	98.2	1.9	43.1	44.7	-12.5	-13.0	27.1	26.2
E1	blue flower	92.1	3.1	55.2	56.5	10.3	8.7	-27.0	-24.8
F1	bluish green	95.2	2.1	69.7	70.6	-30.2	-29.8	-1.4	-3.4
A2	orange	97.5	2.5	61.4	62.6	33.9	31.6	59.9	59.7
B2	purplish blue	95.8	2.9	37.7	38.8	12.1	10.0	-49.5	-48.0
C2	moderate red	96.0	2.8	46.1	47.4	49.2	47.2	14.1	12.6
D2	purple	98.6	1.5	28.3	29.4	23.9	22.9	-25.0	-24.8
E2	yellow green	100.0	0.9	71.3	72.1	-22.5	-22.6	62.2	62.0
F2	orange yellow	98.3	1.9	71.1	72.0	16.2	14.6	70.3	70.8
A3	blue	97.2	2.3	24.2	25.1	16.0	14.2	-55.5	-54.4
B3	green	95.4	3.4	54.5	56.4	-38.7	-38.1	32.5	29.7
C3	red	98.3	1.7	36.7	37.4	54.4	53.7	25.3	23.9
D3	yellow	98.2	2.2	78.9	79.6	6.0	5.3	88.7	90.6
E3	magenta	96.3	2.6	50.0	50.9	50.5	48.5	-19.6	-18.2
F3	cyan	97.5	1.9	51.3	52.5	-23.0	-23.9	-30.3	-29.2
A4	white	71.0	3.3	93.1	93.4	1.8	1.0	-3.5	-0.4
B4	neutral 8	83.0	2.3	78.9	79.7	1.3	0.7	-3.5	-1.5
C4	neutral 6.5	87.5	2.0	65.4	66.4	1.2	0.2	-4.8	-3.4
D4	neutral 5	96.0	1.8	49.8	51.3	1.3	0.5	-3.2	-2.9
E4	neutral 3.5	98.8	1.5	36.6	38.0	1.1	0.5	-2.9	-2.8
F4	black	99.2	1.5	21.8	23.2	1.0	0.5	-1.5	-1.6
A5	paper white	60.2	4.3	96.1	96.0	1.5	0.6	-5.1	-0.9
B5	skin highlight L*=89	85.1	2.5	85.7	86.1	11.6	10.3	6.3	8.4
C5	skin highlight L*=75	94.9	1.7	74.6	75.4	17.7	16.2	11.6	11.9
D5	skin shadow L*=25	95.8	2.0	25.3	26.7	16.9	15.5	14.4	14.1
E5	skin shadow L*=11	95.2	1.6	15.8	16.5	16.9	16.8	10.5	12.0
F5	Max Black	100.0	0.3	6.1	6.4	0.4	0.6	-1.5	-1.5

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

93.5

96.0


2.2

Average Score for the Worst 10%
(3 lowest scoring patches)

71.4


92.8

3.7




AARDENBURG IMAGING
& ARCHIVES

92.2_{color} / 95.6_{tone}



Original Print Colors
(measured before light exposure)




Colors after 60 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*


60 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	91.5	2.8	36.5	38.6	13.2	11.5	10.5	9.6
B1	light Skin	93.4	2.4	65.1	66.7	14.7	13.3	12.6	11.6
C1	blue sky	93.4	2.6	51.5	53.2	-4.1	-5.2	-23.0	-21.3
D1	foliage	96.0	2.6	43.1	45.1	-12.5	-13.1	27.1	25.5
E1	blue flower	90.8	3.5	55.2	56.7	10.3	8.6	-27.0	-24.4
F1	bluish green	92.7	2.9	69.7	70.9	-30.2	-29.5	-1.4	-4.1
A2	orange	96.8	3.1	61.4	62.9	33.9	31.3	59.9	59.0
B2	purplish blue	94.9	3.4	37.7	39.1	12.1	9.7	-49.5	-47.6
C2	moderate red	95.2	3.3	46.1	47.7	49.2	46.9	14.1	12.3
D2	purple	97.5	2.1	28.3	29.8	23.9	22.6	-25.0	-24.5
E2	yellow green	99.5	1.5	71.3	72.5	-22.5	-22.8	62.2	61.4
F2	orange yellow	98.0	2.3	71.1	72.3	16.2	14.3	70.3	70.6
A3	blue	96.3	2.9	24.2	25.5	16.0	13.8	-55.5	-54.1
B3	green	93.0	4.7	54.5	56.9	-38.7	-38.0	32.5	28.5
C3	red	97.6	2.2	36.7	37.7	54.4	53.5	25.3	23.6
D3	yellow	98.0	2.4	78.9	79.9	6.0	5.1	88.7	90.7
E3	magenta	95.7	3.1	50.0	51.2	50.5	48.2	-19.6	-17.9
F3	cyan	97.1	2.2	51.3	52.8	-23.0	-23.9	-30.3	-29.0
A4	white	66.8	3.7	93.1	93.6	1.8	0.9	-3.5	0.0
B4	neutral 8	79.7	2.6	78.9	79.9	1.3	0.6	-3.5	-1.2
C4	neutral 6.5	85.7	2.2	65.4	66.7	1.2	0.2	-4.8	-3.2
D4	neutral 5	95.7	2.1	49.8	51.6	1.3	0.5	-3.2	-2.8
E4	neutral 3.5	98.2	1.8	36.6	38.3	1.1	0.5	-2.9	-2.7
F4	black	98.6	1.8	21.8	23.4	1.0	0.4	-1.5	-1.7
A5	paper white	54.0	4.9	96.1	96.2	1.5	0.5	-5.1	-0.4
B5	skin highlight L*=89	85.0	2.5	85.7	86.3	11.6	10.2	6.3	8.4
C5	skin highlight L*=75	94.7	1.9	74.6	75.6	17.7	16.1	11.6	11.6
D5	skin shadow L*=25	94.0	2.6	25.3	27.2	16.9	15.2	14.4	13.8
E5	skin shadow L*=11	95.9	1.8	15.8	17.1	16.9	16.3	10.5	11.7
F5	Max Black	100.0	1.4	6.1	7.4	0.4	0.7	-1.5	-1.2
Summary Results		I*Color	I*tone	 AARDENBURG IMAGING & ARCHIVES					
Average Score for all patches		92.2	95.6						
Average Score for the Worst 10% (3 lowest scoring patches)		66.8	91.4						

91.1_{color} / 95.0_{tone}



Original Print Colors
(measured before light exposure)




Colors after 70 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*


70 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

				L*		a*		b*	
Column/row	Color Patch	I*Color	ΔE	Before	After	Before	After	Before	After
A1	dark Skin	89.9	3.1	36.5	38.7	13.2	11.3	10.5	9.6
B1	light Skin	91.5	2.7	65.1	66.8	14.7	13.2	12.6	11.6
C1	blue sky	92.5	2.8	51.5	53.3	-4.1	-5.3	-23.0	-21.3
D1	foliage	93.8	3.2	43.1	45.3	-12.5	-13.1	27.1	25.5
E1	blue flower	89.6	3.9	55.2	56.8	10.3	8.5	-27.0	-24.4
F1	bluish green	89.9	3.8	69.7	71.0	-30.2	-29.2	-1.4	-4.1
A2	orange	96.1	3.6	61.4	63.1	33.9	31.1	59.9	59.0
B2	purplish blue	94.6	3.5	37.7	39.0	12.1	9.6	-49.5	-47.6
C2	moderate red	94.6	3.6	46.1	47.8	49.2	46.9	14.1	12.3
D2	purple	97.3	2.2	28.3	29.9	23.9	22.6	-25.0	-24.5
E2	yellow green	98.7	1.9	71.3	72.7	-22.5	-22.9	62.2	61.4
F2	orange yellow	97.8	2.5	71.1	72.5	16.2	14.1	70.3	70.6
A3	blue	95.9	3.2	24.2	25.6	16.0	13.6	-55.5	-54.1
B3	green	90.6	5.9	54.5	57.1	-38.7	-37.8	32.5	28.5
C3	red	97.0	2.6	36.7	37.8	54.4	53.4	25.3	23.6
D3	yellow	97.6	2.8	78.9	79.9	6.0	5.0	88.7	90.7
E3	magenta	95.5	3.2	50.0	51.2	50.5	48.2	-19.6	-17.9
F3	cyan	96.8	2.3	51.3	52.8	-23.0	-23.9	-30.3	-29.0
A4	white	62.7	4.1	93.1	93.6	1.8	0.8	-3.5	0.0
B4	neutral 8	77.3	2.9	78.9	80.0	1.3	0.6	-3.5	-1.2
C4	neutral 6.5	84.9	2.3	65.4	66.7	1.2	0.2	-4.8	-3.2
D4	neutral 5	95.6	2.1	49.8	51.7	1.3	0.5	-3.2	-2.8
E4	neutral 3.5	97.6	1.9	36.6	38.3	1.1	0.4	-2.9	-2.7
F4	black	98.3	1.8	21.8	23.5	1.0	0.4	-1.5	-1.7
A5	paper white	48.2	5.4	96.1	96.1	1.5	0.4	-5.1	-0.4
B5	skin highlight L*=89	86.2	2.4	85.7	86.4	11.6	10.2	6.3	8.4
C5	skin highlight L*=75	94.2	2.1	74.6	75.8	17.7	16.1	11.6	11.6
D5	skin shadow L*=25	92.9	2.9	25.3	27.3	16.9	15.0	14.4	13.8
E5	skin shadow L*=11	95.2	1.9	15.8	17.1	16.9	16.4	10.5	11.7
F5	Max Black	100.0	1.1	6.1	7.1	0.4	0.7	-1.5	-1.2
Summary Results		I*Color	I*tone	 AARDENBURG IMAGING & ARCHIVES					
Average Score for all patches		91.1	95.0						
Average Score for the Worst 10% (3 lowest scoring patches)		62.7	90.1						

90.0_{color} / 94.5_{tone}



Original Print Colors
(measured before light exposure)



Colors after 80 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

80 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	87.5	3.4	36.5	38.8	13.2	11.2	10.5	8.8
B1	light Skin	89.0	3.1	65.1	66.7	14.7	13.0	12.6	10.5
C1	blue sky	91.7	3.0	51.5	53.4	-4.1	-5.4	-23.0	-20.9
D1	foliage	92.3	3.6	43.1	45.4	-12.5	-13.3	27.1	24.4
E1	blue flower	88.3	4.2	55.2	56.8	10.3	8.2	-27.0	-23.7
F1	bluish green	87.5	4.5	69.7	71.0	-30.2	-29.2	-1.4	-5.6
A2	orange	95.3	4.2	61.4	63.3	33.9	30.7	59.9	57.8
B2	purplish blue	93.7	4.0	37.7	39.2	12.1	9.4	-49.5	-47.1
C2	moderate red	93.5	4.2	46.1	47.9	49.2	46.6	14.1	11.3
D2	purple	96.9	2.4	28.3	30.0	23.9	22.4	-25.0	-24.3
E2	yellow green	97.4	2.7	71.3	72.9	-22.5	-23.1	62.2	60.0
F2	orange yellow	97.2	3.0	71.1	72.7	16.2	13.8	70.3	69.8
A3	blue	95.3	3.5	24.2	25.7	16.0	13.4	-55.5	-53.7
B3	green	88.0	7.2	54.5	57.5	-38.7	-37.7	32.5	25.9
C3	red	96.3	3.0	36.7	37.9	54.4	53.3	25.3	22.8
D3	yellow	97.3	3.1	78.9	80.1	6.0	4.6	88.7	91.2
E3	magenta	95.1	3.4	50.0	51.3	50.5	48.0	-19.6	-17.7
F3	cyan	96.6	2.5	51.3	53.0	-23.0	-24.0	-30.3	-28.8
A4	white	60.3	4.3	93.1	93.6	1.8	0.8	-3.5	0.6
B4	neutral 8	76.1	3.0	78.9	80.1	1.3	0.7	-3.5	-0.9
C4	neutral 6.5	84.6	2.4	65.4	66.8	1.2	0.2	-4.8	-3.1
D4	neutral 5	95.9	2.3	49.8	51.9	1.3	0.4	-3.2	-3.0
E4	neutral 3.5	97.7	2.1	36.6	38.5	1.1	0.4	-2.9	-2.8
F4	black	97.2	2.0	21.8	23.6	1.0	0.3	-1.5	-1.8
A5	paper white	44.0	5.8	96.1	96.1	1.5	0.3	-5.1	0.6
B5	skin highlight L*=89	86.3	2.4	85.7	86.4	11.6	10.1	6.3	8.1
C5	skin highlight L*=75	92.4	2.4	74.6	75.9	17.7	16.0	11.6	10.4
D5	skin shadow L*=25	91.8	3.2	25.3	27.5	16.9	14.9	14.4	13.4
E5	skin shadow L*=11	94.3	2.2	15.8	17.3	16.9	16.3	10.5	12.1
F5	Max Black	100.0	1.2	6.1	7.3	0.4	0.7	-1.5	-1.4

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

90.0

94.5


3.3

**Average Score for the Worst 10%
(3 lowest scoring patches)**

60.1


89.2

5.8




AARDENBURG IMAGING
& ARCHIVES

88.7^{color} / 93.9^{tone}



Original Print Colors
(measured before light exposure)



Colors after 90 Megalux-hours
light exposure


*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

90 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)


				L*		a*		b*	
Column/row	Color Patch	I*Color	ΔE	Before	After	Before	After	Before	After
A1	dark Skin	85.8	3.8	36.5	39.1	13.2	11.1	10.5	8.5
B1	light Skin	86.0	3.8	65.1	67.1	14.7	13.0	12.6	9.9
C1	blue sky	90.5	3.4	51.5	53.6	-4.1	-5.5	-23.0	-20.7
D1	foliage	89.8	4.4	43.1	45.7	-12.5	-13.3	27.1	23.6
E1	blue flower	86.7	4.7	55.2	57.0	10.3	8.1	-27.0	-23.3
F1	bluish green	84.2	5.5	69.7	71.2	-30.2	-28.8	-1.4	-6.5
A2	orange	94.1	5.0	61.4	63.6	33.9	30.4	59.9	57.0
B2	purplish blue	93.2	4.3	37.7	39.3	12.1	9.1	-49.5	-46.9
C2	moderate red	92.7	4.7	46.1	48.1	49.2	46.5	14.1	10.9
D2	purple	96.5	2.6	28.3	30.2	23.9	22.4	-25.0	-24.2
E2	yellow green	96.3	3.5	71.3	73.2	-22.5	-23.3	62.2	59.3
F2	orange yellow	96.7	3.4	71.1	73.0	16.2	13.5	70.3	69.4
A3	blue	94.8	3.9	24.2	25.8	16.0	13.1	-55.5	-53.5
B3	green	85.6	8.5	54.5	57.8	-38.7	-37.6	32.5	24.8
C3	red	95.9	3.3	36.7	38.1	54.4	53.3	25.3	22.5
D3	yellow	97.0	3.5	78.9	80.4	6.0	4.4	88.7	91.4
E3	magenta	94.7	3.6	50.0	51.4	50.5	47.8	-19.6	-17.6
F3	cyan	96.1	2.8	51.3	53.2	-23.0	-24.1	-30.3	-28.6
A4	white	56.8	4.6	93.1	93.7	1.8	0.7	-3.5	0.9
B4	neutral 8	73.7	3.3	78.9	80.2	1.3	0.6	-3.5	-0.6
C4	neutral 6.5	83.5	2.6	65.4	67.0	1.2	0.1	-4.8	-3.0
D4	neutral 5	95.7	2.5	49.8	52.1	1.3	0.4	-3.2	-3.0
E4	neutral 3.5	97.9	2.3	36.6	38.8	1.1	0.4	-2.9	-2.9
F4	black	96.7	2.2	21.8	23.8	1.0	0.3	-1.5	-1.9
A5	paper white	39.6	6.2	96.1	96.2	1.5	0.2	-5.1	1.0
B5	skin highlight L*=89	87.0	2.4	85.7	86.6	11.6	10.1	6.3	7.9
C5	skin highlight L*=75	90.6	2.9	74.6	76.1	17.7	16.0	11.6	9.9
D5	skin shadow L*=25	90.4	3.7	25.3	27.8	16.9	14.7	14.4	13.1
E5	skin shadow L*=11	93.4	2.5	15.8	17.5	16.9	16.2	10.5	12.2
F5	Max Black	100.0	1.3	6.1	7.4	0.4	0.7	-1.5	-1.4
Summary Results		I*Color	I*tone	ΔE	AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		88.7	93.9	3.7					
Average Score for the Worst 10% (3 lowest scoring patches)		56.7	88.1	6.7					

Page 14

87.5_{color} / 93.4_{tone}



Original Print Colors
(measured before light exposure)



Colors after 100 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

100 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	84.2	4.1	36.5	39.2	13.2	11.1	10.5	8.1
B1	light Skin	82.3	4.5	65.1	67.3	14.7	13.0	12.6	9.0
C1	blue sky	89.8	3.6	51.5	53.7	-4.1	-5.6	-23.0	-20.5
D1	foliage	87.9	4.9	43.1	45.8	-12.5	-13.3	27.1	23.1
E1	blue flower	85.4	5.1	55.2	57.1	10.3	8.0	-27.0	-23.0
F1	bluish green	80.7	6.5	69.7	71.4	-30.2	-28.5	-1.4	-7.5
A2	orange	93.4	5.6	61.4	63.7	33.9	30.2	59.9	56.3
B2	purplish blue	92.2	4.8	37.7	39.4	12.1	8.7	-49.5	-46.6
C2	moderate red	92.0	5.0	46.1	48.3	49.2	46.5	14.1	10.4
D2	purple	96.9	2.4	28.3	30.0	23.9	22.4	-25.0	-24.3
E2	yellow green	95.1	4.3	71.3	73.4	-22.5	-23.4	62.2	58.6
F2	orange yellow	96.2	3.8	71.1	73.2	16.2	13.3	70.3	69.0
A3	blue	94.6	3.9	24.2	25.6	16.0	12.8	-55.5	-53.7
B3	green	83.2	9.7	54.5	58.0	-38.7	-37.7	32.5	23.5
C3	red	95.9	3.3	36.7	38.1	54.4	53.7	25.3	22.4
D3	yellow	96.3	4.1	78.9	80.5	6.0	4.2	88.7	92.0
E3	magenta	94.6	3.7	50.0	51.5	50.5	47.8	-19.6	-17.5
F3	cyan	95.5	3.0	51.3	53.3	-23.0	-24.3	-30.3	-28.5
A4	white	53.0	5.0	93.1	93.8	1.8	0.6	-3.5	1.3
B4	neutral 8	72.2	3.5	78.9	80.4	1.3	0.7	-3.5	-0.5
C4	neutral 6.5	82.7	2.7	65.4	67.1	1.2	0.1	-4.8	-2.9
D4	neutral 5	96.0	2.6	49.8	52.2	1.3	0.4	-3.2	-3.1
E4	neutral 3.5	97.7	2.4	36.6	38.8	1.1	0.4	-2.9	-2.9
F4	black	95.0	2.0	21.8	23.6	1.0	0.2	-1.5	-2.0
A5	paper white	35.0	6.7	96.1	96.2	1.5	0.1	-5.1	1.4
B5	skin highlight L*=89	88.8	2.2	85.7	86.7	11.6	10.1	6.3	7.6
C5	skin highlight L*=75	87.8	3.5	74.6	76.2	17.7	16.1	11.6	9.0
D5	skin shadow L*=25	90.8	3.6	25.3	27.8	16.9	14.7	14.4	13.2
E5	skin shadow L*=11	89.8	2.8	15.8	17.1	16.9	16.8	10.5	13.1
F5	Max Black	100.0	0.1	6.1	6.2	0.4	0.6	-1.5	-1.6

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

87.5

93.4


4.0

**Average Score for the Worst 10%
(3 lowest scoring patches)**

53.4


87.1

7.6




AARDENBURG IMAGING
& ARCHIVES

86.4_{color} / 93.0_{tone}



Original Print Colors
(measured before light exposure)




Colors after 110 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

110 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	82.2	4.5	36.5	39.3	13.2	11.1	10.5	7.7
B1	light Skin	78.6	5.2	65.1	67.4	14.7	13.1	12.6	8.2
C1	blue sky	89.3	3.7	51.5	53.7	-4.1	-5.6	-23.0	-20.4
D1	foliage	85.5	5.6	43.1	45.9	-12.5	-13.3	27.1	22.3
E1	blue flower	84.4	5.4	55.2	57.2	10.3	7.9	-27.0	-22.6
F1	bluish green	77.5	7.5	69.7	71.4	-30.2	-28.1	-1.4	-8.5
A2	orange	92.2	6.4	61.4	63.9	33.9	29.9	59.9	55.6
B2	purplish blue	91.9	4.9	37.7	39.3	12.1	8.7	-49.5	-46.5
C2	moderate red	91.0	5.6	46.1	48.3	49.2	46.3	14.1	9.9
D2	purple	96.6	2.4	28.3	30.0	23.9	22.4	-25.0	-24.2
E2	yellow green	93.6	5.2	71.3	73.5	-22.5	-23.5	62.2	57.6
F2	orange yellow	95.4	4.3	71.1	73.2	16.2	13.0	70.3	68.3
A3	blue	94.0	4.2	24.2	25.6	16.0	12.6	-55.5	-53.5
B3	green	80.3	11.1	54.5	58.2	-38.7	-37.6	32.5	22.1
C3	red	95.3	3.6	36.7	38.2	54.4	53.6	25.3	22.1
D3	yellow	96.2	4.2	78.9	80.5	6.0	4.0	88.7	92.0
E3	magenta	94.5	3.7	50.0	51.3	50.5	47.8	-19.6	-17.5
F3	cyan	95.3	3.0	51.3	53.2	-23.0	-24.3	-30.3	-28.4
A4	white	50.1	5.3	93.1	93.6	1.8	0.6	-3.5	1.6
B4	neutral 8	71.5	3.5	78.9	80.2	1.3	0.7	-3.5	-0.4
C4	neutral 6.5	82.3	2.7	65.4	67.0	1.2	0.2	-4.8	-2.9
D4	neutral 5	96.2	2.6	49.8	52.2	1.3	0.4	-3.2	-3.2
E4	neutral 3.5	98.2	2.3	36.6	38.8	1.1	0.4	-2.9	-3.0
F4	black	95.0	2.0	21.8	23.6	1.0	0.2	-1.5	-2.1
A5	paper white	31.7	7.0	96.1	95.9	1.5	0.1	-5.1	1.7
B5	skin highlight L*=89	90.4	1.9	85.7	86.5	11.6	10.1	6.3	7.3
C5	skin highlight L*=75	84.4	4.1	74.6	76.1	17.7	16.1	11.6	8.2
D5	skin shadow L*=25	90.0	3.7	25.3	27.8	16.9	14.7	14.4	12.9
E5	skin shadow L*=11	89.0	3.0	15.8	17.2	16.9	16.8	10.5	13.2
F5	Max Black	100.0	0.2	6.1	5.9	0.4	0.5	-1.5	-1.6
Summary Results		I*Color	I*tone	 AARDENBURG IMAGING & ARCHIVES					
Average Score for all patches		86.4	93.0						
Average Score for the Worst 10% (3 lowest scoring patches)		51.1	86.3						

85.2_{color} / 92.5_{tone}



Original Print Colors
(measured before light exposure)



Colors after 120 Megalux-hours
light exposure


*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

120 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	80.0	4.9	36.5	39.6	13.2	11.0	10.5	7.3
B1	light Skin	74.8	5.9	65.1	67.5	14.7	13.1	12.6	7.5
C1	blue sky	88.6	3.9	51.5	53.9	-4.1	-5.7	-23.0	-20.3
D1	foliage	82.3	6.6	43.1	46.2	-12.5	-13.3	27.1	21.4
E1	blue flower	83.4	5.7	55.2	57.4	10.3	7.8	-27.0	-22.4
F1	bluish green	74.4	8.4	69.7	71.6	-30.2	-27.7	-1.4	-9.3
A2	orange	90.5	7.5	61.4	64.2	33.9	29.7	59.9	54.2
B2	purplish blue	91.4	5.2	37.7	39.5	12.1	8.5	-49.5	-46.2
C2	moderate red	90.0	6.1	46.1	48.6	49.2	46.2	14.1	9.4
D2	purple	95.8	2.8	28.3	30.3	23.9	22.2	-25.0	-24.0
E2	yellow green	91.7	6.4	71.3	73.7	-22.5	-23.5	62.2	56.3
F2	orange yellow	94.5	5.0	71.1	73.4	16.2	12.8	70.3	67.4
A3	blue	93.4	4.6	24.2	25.8	16.0	12.4	-55.5	-53.2
B3	green	77.8	12.4	54.5	58.5	-38.7	-37.4	32.5	20.8
C3	red	94.6	4.1	36.7	38.4	54.4	53.6	25.3	21.7
D3	yellow	95.9	4.4	78.9	80.6	6.0	3.8	88.7	92.1
E3	magenta	94.1	4.0	50.0	51.5	50.5	47.6	-19.6	-17.3
F3	cyan	94.9	3.2	51.3	53.4	-23.0	-24.3	-30.3	-28.2
A4	white	48.0	5.5	93.1	93.7	1.8	0.6	-3.5	1.8
B4	neutral 8	69.7	3.7	78.9	80.4	1.3	0.7	-3.5	-0.2
C4	neutral 6.5	81.7	2.8	65.4	67.1	1.2	0.2	-4.8	-2.8
D4	neutral 5	96.3	2.8	49.8	52.5	1.3	0.5	-3.2	-3.3
E4	neutral 3.5	98.1	2.5	36.6	39.0	1.1	0.4	-2.9	-3.0
F4	black	94.2	2.2	21.8	23.8	1.0	0.2	-1.5	-2.1
A5	paper white	28.5	7.3	96.1	96.0	1.5	0.0	-5.1	2.0
B5	skin highlight L*=89	90.8	2.0	85.7	86.7	11.6	10.1	6.3	7.1
C5	skin highlight L*=75	81.8	4.7	74.6	76.3	17.7	16.2	11.6	7.6
D5	skin shadow L*=25	89.0	4.1	25.3	28.1	16.9	14.6	14.4	12.6
E5	skin shadow L*=11	89.4	3.1	15.8	17.5	16.9	16.6	10.5	13.1
F5	Max Black	100.0	0.1	6.1	6.1	0.4	0.5	-1.5	-1.6


Summary Results

I*Color	I*tone	ΔE
85.2	92.5	4.7
48.7	85.6	9.4



AARDENBURG IMAGING
& ARCHIVES

84.1_{color} / 91.9_{tone}



Original Print Colors
(measured before light exposure)



Colors after 130 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

130 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	78.9	5.2	36.5	39.9	13.2	10.9	10.5	7.1
B1	light Skin	71.3	6.6	65.1	67.8	14.7	13.1	12.6	6.7
C1	blue sky	87.7	4.2	51.5	54.1	-4.1	-5.7	-23.0	-20.0
D1	foliage	78.7	7.7	43.1	46.6	-12.5	-13.2	27.1	20.3
E1	blue flower	82.4	6.1	55.2	57.6	10.3	7.7	-27.0	-22.1
F1	bluish green	72.0	9.2	69.7	71.7	-30.2	-27.4	-1.4	-10.0
A2	orange	88.9	8.7	61.4	64.5	33.9	29.5	59.9	53.0
B2	purplish blue	90.9	5.5	37.7	39.6	12.1	8.4	-49.5	-46.0
C2	moderate red	89.2	6.6	46.1	48.8	49.2	46.2	14.1	8.9
D2	purple	95.4	3.0	28.3	30.5	23.9	22.2	-25.0	-23.8
E2	yellow green	90.1	7.5	71.3	73.9	-22.5	-23.6	62.2	55.2
F2	orange yellow	93.6	5.7	71.1	73.7	16.2	12.6	70.3	66.6
A3	blue	93.0	4.9	24.2	25.9	16.0	12.2	-55.5	-53.1
B3	green	75.4	13.6	54.5	58.8	-38.7	-37.1	32.5	19.6
C3	red	94.2	4.5	36.7	38.7	54.4	53.6	25.3	21.4
D3	yellow	95.7	4.7	78.9	80.8	6.0	3.6	88.7	92.3
E3	magenta	93.7	4.3	50.0	51.7	50.5	47.5	-19.6	-17.1
F3	cyan	94.6	3.5	51.3	53.6	-23.0	-24.3	-30.3	-28.1
A4	white	45.6	5.7	93.1	93.8	1.8	0.5	-3.5	2.0
B4	neutral 8	67.1	4.0	78.9	80.6	1.3	0.8	-3.5	0.0
C4	neutral 6.5	80.9	3.0	65.4	67.3	1.2	0.2	-4.8	-2.7
D4	neutral 5	97.4	3.0	49.8	52.7	1.3	0.6	-3.2	-3.2
E4	neutral 3.5	98.9	2.8	36.6	39.3	1.1	0.5	-2.9	-3.0
F4	black	93.9	2.5	21.8	24.0	1.0	0.2	-1.5	-2.2
A5	paper white	25.0	7.6	96.1	96.1	1.5	0.0	-5.1	2.4
B5	skin highlight L*=89	92.3	1.9	85.7	86.9	11.6	10.2	6.3	6.8
C5	skin highlight L*=75	79.2	5.3	74.6	76.5	17.7	16.3	11.6	6.9
D5	skin shadow L*=25	87.9	4.6	25.3	28.7	16.9	14.5	14.4	12.4
E5	skin shadow L*=11	89.1	3.4	15.8	17.9	16.9	16.6	10.5	13.2
F5	Max Black	100.0	0.3	6.1	6.3	0.4	0.6	-1.5	-1.5

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

84.1

91.9


5.2

Average Score for the Worst 10%
(3 lowest scoring patches)

45.9


84.9

10.5




AARDENBURG IMAGING
& ARCHIVES

83.0_{color} / 91.3_{tone}



Original Print Colors
(measured before light exposure)




Colors after 140 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*


140 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	77.1	5.6	36.5	40.1	13.2	10.9	10.5	6.7
B1	light Skin	67.5	7.4	65.1	68.0	14.7	13.2	12.6	6.0
C1	blue sky	87.2	4.4	51.5	54.3	-4.1	-5.7	-23.0	-19.9
D1	foliage	75.9	8.5	43.1	46.8	-12.5	-13.1	27.1	19.4
E1	blue flower	81.6	6.3	55.2	57.7	10.3	7.7	-27.0	-21.9
F1	bluish green	69.3	10.0	69.7	71.9	-30.2	-27.1	-1.4	-10.7
A2	orange	87.1	9.9	61.4	64.7	33.9	29.2	59.9	51.7
B2	purplish blue	90.6	5.7	37.7	39.7	12.1	8.3	-49.5	-45.8
C2	moderate red	88.3	7.1	46.1	49.1	49.2	46.1	14.1	8.4
D2	purple	94.9	3.3	28.3	30.7	23.9	22.1	-25.0	-23.6
E2	yellow green	88.0	8.9	71.3	74.2	-22.5	-23.6	62.2	53.8
F2	orange yellow	92.3	6.7	71.1	73.9	16.2	12.4	70.3	65.6
A3	blue	92.3	5.3	24.2	26.1	16.0	11.9	-55.5	-52.8
B3	green	72.6	15.0	54.5	59.1	-38.7	-36.8	32.5	18.2
C3	red	93.6	4.9	36.7	38.9	54.4	53.6	25.3	21.0
D3	yellow	95.8	4.7	78.9	81.0	6.0	3.3	88.7	92.0
E3	magenta	93.5	4.4	50.0	51.8	50.5	47.4	-19.6	-17.0
F3	cyan	94.4	3.6	51.3	53.8	-23.0	-24.3	-30.3	-28.0
A4	white	44.4	5.8	93.1	93.8	1.8	0.5	-3.5	2.1
B4	neutral 8	66.0	4.2	78.9	80.7	1.3	0.8	-3.5	0.2
C4	neutral 6.5	80.5	3.1	65.4	67.4	1.2	0.3	-4.8	-2.6
D4	neutral 5	98.0	3.2	49.8	52.8	1.3	0.6	-3.2	-3.2
E4	neutral 3.5	99.3	3.0	36.6	39.5	1.1	0.6	-2.9	-3.0
F4	black	93.4	2.6	21.8	24.1	1.0	0.2	-1.5	-2.3
A5	paper white	22.1	7.9	96.1	96.1	1.5	0.0	-5.1	2.6
B5	skin highlight L*=89	92.7	1.9	85.7	87.0	11.6	10.2	6.3	6.5
C5	skin highlight L*=75	76.0	5.9	74.6	76.7	17.7	16.3	11.6	6.2
D5	skin shadow L*=25	86.8	5.0	25.3	29.0	16.9	14.4	14.4	12.1
E5	skin shadow L*=11	88.3	3.7	15.8	18.1	16.9	16.6	10.5	13.4
F5	Max Black	100.0	0.4	6.1	6.4	0.4	0.6	-1.5	-1.6
Summary Results		I*Color	I*tone	 AARDENBURG IMAGING & ARCHIVES					
Average Score for all patches		83.0	91.3						
Average Score for the Worst 10% (3 lowest scoring patches)		44.2	83.7						

81.9_{color} / 90.6_{tone}



Original Print Colors
(measured before light exposure)



Colors after 150 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

150 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	75.2	6.1	36.5	40.4	13.2	11.0	10.5	6.4
B1	light Skin	63.7	8.1	65.1	68.2	14.7	13.3	12.6	5.2
C1	blue sky	86.8	4.6	51.5	54.4	-4.1	-5.6	-23.0	-19.7
D1	foliage	72.8	9.4	43.1	47.0	-12.5	-12.9	27.1	18.5
E1	blue flower	80.5	6.7	55.2	57.9	10.3	7.6	-27.0	-21.5
F1	bluish green	66.9	10.7	69.7	72.0	-30.2	-26.7	-1.4	-11.3
A2	orange	85.3	11.2	61.4	65.1	33.9	29.0	59.9	50.4
B2	purplish blue	89.8	6.1	37.7	39.8	12.1	8.1	-49.5	-45.5
C2	moderate red	87.4	7.6	46.1	49.3	49.2	46.0	14.1	8.0
D2	purple	94.6	3.5	28.3	30.8	23.9	22.1	-25.0	-23.5
E2	yellow green	85.4	10.6	71.3	74.4	-22.5	-23.6	62.2	52.1
F2	orange yellow	90.6	7.9	71.1	74.2	16.2	12.2	70.3	64.3
A3	blue	92.2	5.4	24.2	26.2	16.0	11.9	-55.5	-52.7
B3	green	69.5	16.6	54.5	59.4	-38.7	-36.5	32.5	16.7
C3	red	93.0	5.3	36.7	39.2	54.4	53.5	25.3	20.7
D3	yellow	95.9	4.7	78.9	81.2	6.0	3.0	88.7	91.6
E3	magenta	93.2	4.6	50.0	51.9	50.5	47.3	-19.6	-16.9
F3	cyan	94.2	3.8	51.3	53.9	-23.0	-24.2	-30.3	-27.9
A4	white	43.4	5.9	93.1	93.9	1.8	0.5	-3.5	2.2
B4	neutral 8	65.1	4.3	78.9	80.8	1.3	0.9	-3.5	0.3
C4	neutral 6.5	80.3	3.2	65.4	67.5	1.2	0.4	-4.8	-2.6
D4	neutral 5	99.1	3.4	49.8	53.1	1.3	0.7	-3.2	-3.2
E4	neutral 3.5	100.0	3.2	36.6	39.7	1.1	0.7	-2.9	-3.1
F4	black	93.5	2.8	21.8	24.4	1.0	0.3	-1.5	-2.4
A5	paper white	19.9	8.1	96.1	96.1	1.5	-0.1	-5.1	2.8
B5	skin highlight L*=89	93.0	2.0	85.7	87.1	11.6	10.2	6.3	6.2
C5	skin highlight L*=75	72.7	6.6	74.6	76.8	17.7	16.4	11.6	5.5
D5	skin shadow L*=25	86.4	5.4	25.3	29.3	16.9	14.4	14.4	12.0
E5	skin shadow L*=11	87.6	4.0	15.8	18.4	16.9	16.6	10.5	13.5
F5	Max Black	100.0	0.4	6.1	6.4	0.4	0.6	-1.5	-1.6

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

81.9

90.6


6.1

Average Score for the Worst 10%
(3 lowest scoring patches)

42.4


82.5

12.9



AARDENBURG IMAGING
& ARCHIVES

80.7_{color} / 90.2_{tone}



Original Print Colors
(measured before light exposure)



Colors after 160 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

160 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	73.7	6.5	36.5	40.7	13.2	11.0	10.5	6.0
B1	light Skin	60.1	8.9	65.1	68.4	14.7	13.5	12.6	4.4
C1	blue sky	85.9	4.9	51.5	54.6	-4.1	-5.6	-23.0	-19.5
D1	foliage	70.4	10.2	43.1	47.2	-12.5	-12.7	27.1	17.8
E1	blue flower	79.4	7.1	55.2	58.1	10.3	7.6	-27.0	-21.2
F1	bluish green	65.3	11.2	69.7	72.0	-30.2	-26.3	-1.4	-11.7
A2	orange	83.2	12.7	61.4	65.3	33.9	28.7	59.9	49.0
B2	purplish blue	88.4	6.8	37.7	40.1	12.1	7.8	-49.5	-44.8
C2	moderate red	86.5	8.2	46.1	49.6	49.2	45.8	14.1	7.6
D2	purple	93.6	3.9	28.3	31.0	23.9	21.9	-25.0	-23.1
E2	yellow green	82.8	12.3	71.3	74.5	-22.5	-23.5	62.2	50.3
F2	orange yellow	88.8	9.2	71.1	74.4	16.2	12.0	70.3	62.9
A3	blue	91.1	6.1	24.2	26.4	16.0	11.5	-55.5	-52.2
B3	green	66.9	18.0	54.5	59.6	-38.7	-36.1	32.5	15.4
C3	red	92.6	5.7	36.7	39.4	54.4	53.5	25.3	20.5
D3	yellow	96.2	4.6	78.9	81.4	6.0	2.8	88.7	91.0
E3	magenta	92.8	4.8	50.0	52.0	50.5	47.2	-19.6	-16.7
F3	cyan	93.7	4.0	51.3	54.0	-23.0	-24.2	-30.3	-27.7
A4	white	40.5	6.2	93.1	93.8	1.8	0.5	-3.5	2.5
B4	neutral 8	63.5	4.5	78.9	80.9	1.3	1.0	-3.5	0.4
C4	neutral 6.5	79.0	3.3	65.4	67.6	1.2	0.4	-4.8	-2.4
D4	neutral 5	100.0	3.5	49.8	53.2	1.3	0.8	-3.2	-3.2
E4	neutral 3.5	100.0	3.3	36.6	39.9	1.1	0.7	-2.9	-3.0
F4	black	93.9	3.0	21.8	24.5	1.0	0.3	-1.5	-2.3
A5	paper white	17.8	8.3	96.1	96.1	1.5	-0.2	-5.1	3.0
B5	skin highlight L*=89	92.6	2.1	85.7	87.2	11.6	10.2	6.3	5.9
C5	skin highlight L*=75	69.6	7.3	74.6	76.9	17.7	16.5	11.6	4.8
D5	skin shadow L*=25	86.1	5.6	25.3	29.6	16.9	14.4	14.4	11.8
E5	skin shadow L*=11	86.0	4.4	15.8	18.7	16.9	16.6	10.5	13.8
F5	Max Black	100.0	0.4	6.1	6.5	0.4	0.5	-1.5	-1.5

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

80.7

90.2


6.6

Average Score for the Worst 10%
(3 lowest scoring patches)

39.4


82.2

14.3



AARDENBURG IMAGING
& ARCHIVES

78.6_{color} / 88.9_{tone}



Original Print Colors
(measured before light exposure)



Colors after 180 Megalux-hours
light exposure


*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

180 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	71.1	7.2	36.5	41.4	13.2	11.2	10.5	5.5
B1	light Skin	54.7	10.0	65.1	68.9	14.7	13.7	12.6	3.4
C1	blue sky	84.8	5.3	51.5	55.0	-4.1	-5.5	-23.0	-19.2
D1	foliage	64.8	11.9	43.1	47.8	-12.5	-12.5	27.1	16.1
E1	blue flower	77.8	7.7	55.2	58.5	10.3	7.6	-27.0	-20.7
F1	bluish green	61.9	12.3	69.7	72.4	-30.2	-25.8	-1.4	-12.6
A2	orange	79.3	15.4	61.4	66.1	33.9	28.4	59.9	46.2
B2	purplish blue	87.6	7.3	37.7	40.4	12.1	7.5	-49.5	-44.5
C2	moderate red	84.9	9.2	46.1	50.3	49.2	45.8	14.1	6.7
D2	purple	93.0	4.4	28.3	31.5	23.9	22.0	-25.0	-22.8
E2	yellow green	77.3	16.0	71.3	75.0	-22.5	-23.4	62.2	46.7
F2	orange yellow	85.2	11.8	71.1	74.9	16.2	11.7	70.3	60.0
A3	blue	90.2	6.6	24.2	26.6	16.0	11.0	-55.5	-52.0
B3	green	62.1	20.4	54.5	60.1	-38.7	-35.6	32.5	13.1
C3	red	91.6	6.5	36.7	40.0	54.4	53.7	25.3	19.8
D3	yellow	96.2	4.8	78.9	81.8	6.0	2.4	88.7	90.1
E3	magenta	92.5	5.1	50.0	52.4	50.5	47.2	-19.6	-16.5
F3	cyan	93.0	4.4	51.3	54.3	-23.0	-24.2	-30.3	-27.3
A4	white	38.2	6.4	93.1	94.0	1.8	0.5	-3.5	2.7
B4	neutral 8	60.3	4.9	78.9	81.3	1.3	1.2	-3.5	0.7
C4	neutral 6.5	76.9	3.7	65.4	68.0	1.2	0.7	-4.8	-2.2
D4	neutral 5	100.0	3.9	49.8	53.7	1.3	1.1	-3.2	-3.1
E4	neutral 3.5	100.0	3.8	36.6	40.4	1.1	1.0	-2.9	-2.9
F4	black	93.9	3.3	21.8	24.9	1.0	0.5	-1.5	-2.5
A5	paper white	13.0	8.8	96.1	96.1	1.5	-0.2	-5.1	3.5
B5	skin highlight L*=89	91.8	2.3	85.7	87.4	11.6	10.3	6.3	5.4
C5	skin highlight L*=75	65.2	8.3	74.6	77.2	17.7	16.8	11.6	3.8
D5	skin shadow L*=25	84.8	6.5	25.3	30.5	16.9	14.4	14.4	11.4
E5	skin shadow L*=11	85.4	4.9	15.8	19.4	16.9	16.7	10.5	13.9
F5	Max Black	100.0	0.3	6.1	6.3	0.4	0.6	-1.5	-1.4


Summary Results

	I*Color	I*tone	ΔE
Average Score for all patches	78.6	88.9	7.5
Average Score for the Worst 10% (3 lowest scoring patches)	35.3	80.6	17.3



AARDENBURG IMAGING
& ARCHIVES

77.0_{color} / 87.9_{tone}




Original Print Colors
(measured before light exposure)




Colors after 200 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

200 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	69.5	7.8	36.5	41.9	13.2	11.3	10.5	5.2
B1	light Skin	51.9	10.6	65.1	69.1	14.7	13.8	12.6	2.8
C1	blue sky	83.2	5.8	51.5	55.3	-4.1	-5.4	-23.0	-18.7
D1	foliage	59.5	13.6	43.1	48.3	-12.5	-12.1	27.1	14.5
E1	blue flower	76.6	8.1	55.2	58.8	10.3	7.6	-27.0	-20.3
F1	bluish green	59.8	12.9	69.7	72.6	-30.2	-25.3	-1.4	-13.1
A2	orange	75.8	17.9	61.4	66.7	33.9	28.1	59.9	43.7
B2	purplish blue	87.2	7.6	37.7	40.5	12.1	7.5	-49.5	-44.3
C2	moderate red	83.9	9.9	46.1	50.7	49.2	45.8	14.1	6.1
D2	purple	92.0	4.9	28.3	31.9	23.9	22.0	-25.0	-22.4
E2	yellow green	72.8	18.9	71.3	75.4	-22.5	-23.3	62.2	43.7
F2	orange yellow	81.9	14.2	71.1	75.3	16.2	11.5	70.3	57.6
A3	blue	89.6	7.0	24.2	26.9	16.0	10.8	-55.5	-51.7
B3	green	58.1	22.5	54.5	60.6	-38.7	-34.9	32.5	11.1
C3	red	90.8	7.2	36.7	40.6	54.4	53.8	25.3	19.3
D3	yellow	96.0	5.2	78.9	82.2	6.0	1.9	88.7	88.9
E3	magenta	92.2	5.4	50.0	52.7	50.5	47.2	-19.6	-16.3
F3	cyan	92.5	4.7	51.3	54.5	-23.0	-24.0	-30.3	-27.1
A4	white	37.9	6.5	93.1	94.0	1.8	0.5	-3.5	2.7
B4	neutral 8	58.3	5.2	78.9	81.5	1.3	1.3	-3.5	0.9
C4	neutral 6.5	75.3	4.0	65.4	68.2	1.2	0.9	-4.8	-2.0
D4	neutral 5	100.0	4.2	49.8	54.0	1.3	1.3	-3.2	-3.0
E4	neutral 3.5	100.0	4.2	36.6	40.8	1.1	1.2	-2.9	-2.9
F4	black	94.1	3.6	21.8	25.3	1.0	0.6	-1.5	-2.5
A5	paper white	10.1	9.0	96.1	96.2	1.5	-0.2	-5.1	3.8
B5	skin highlight L*=89	90.0	2.7	85.7	87.7	11.6	10.4	6.3	5.0
C5	skin highlight L*=75	62.6	8.9	74.6	77.5	17.7	16.9	11.6	3.2
D5	skin shadow L*=25	83.7	7.2	25.3	31.2	16.9	14.4	14.4	11.1
E5	skin shadow L*=11	84.4	5.4	15.8	19.9	16.9	16.7	10.5	14.1
F5	Max Black	100.0	0.6	6.1	6.6	0.4	0.6	-1.5	-1.4
Summary Results		I*Color	I*tone	 AARDENBURG IMAGING & ARCHIVES					
Average Score for all patches		77.0	87.9						
Average Score for the Worst 10% (3 lowest scoring patches)		33.3	79.4						

75.4_{color} / 86.4_{tone}



Original Print Colors
(measured before light exposure)




Colors after 220 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

220 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	68.6	8.4	36.5	42.7	13.2	11.3	10.5	5.0
B1	light Skin	48.5	11.4	65.1	69.6	14.7	13.9	12.6	2.1
C1	blue sky	81.3	6.4	51.5	55.7	-4.1	-5.4	-23.0	-18.3
D1	foliage	55.3	15.0	43.1	48.9	-12.5	-11.9	27.1	13.3
E1	blue flower	75.3	8.7	55.2	59.2	10.3	7.7	-27.0	-19.8
F1	bluish green	59.0	13.2	69.7	72.8	-30.2	-24.9	-1.4	-13.2
A2	orange	72.6	20.3	61.4	67.4	33.9	27.7	59.9	41.5
B2	purplish blue	86.5	8.0	37.7	40.8	12.1	7.4	-49.5	-43.9
C2	moderate red	82.8	10.7	46.1	51.4	49.2	45.7	14.1	5.5
D2	purple	90.9	5.5	28.3	32.4	23.9	22.1	-25.0	-21.8
E2	yellow green	67.2	22.7	71.3	75.8	-22.5	-23.0	62.2	40.0
F2	orange yellow	78.1	16.9	71.1	75.8	16.2	11.3	70.3	54.7
A3	blue	89.1	7.4	24.2	27.0	16.0	10.5	-55.5	-51.5
B3	green	54.9	24.1	54.5	61.0	-38.7	-34.5	32.5	9.6
C3	red	89.8	8.0	36.7	41.2	54.4	53.9	25.3	18.7
D3	yellow	95.4	5.9	78.9	82.6	6.0	1.5	88.7	87.9
E3	magenta	91.9	5.7	50.0	53.0	50.5	47.1	-19.6	-16.1
F3	cyan	91.8	5.1	51.3	54.8	-23.0	-23.9	-30.3	-26.8
A4	white	37.7	6.5	93.1	94.1	1.8	0.5	-3.5	2.8
B4	neutral 8	56.0	5.5	78.9	81.7	1.3	1.5	-3.5	1.1
C4	neutral 6.5	73.0	4.3	65.4	68.5	1.2	1.1	-4.8	-1.7
D4	neutral 5	99.6	4.5	49.8	54.3	1.3	1.6	-3.2	-2.8
E4	neutral 3.5	100.0	4.7	36.6	41.3	1.1	1.5	-2.9	-2.7
F4	black	95.3	3.9	21.8	25.6	1.0	0.9	-1.5	-2.5
A5	paper white	9.7	9.1	96.1	96.1	1.5	-0.3	-5.1	3.8
B5	skin highlight L*=89	87.0	3.1	85.7	87.9	11.6	10.4	6.3	4.5
C5	skin highlight L*=75	59.9	9.5	74.6	77.7	17.7	17.1	11.6	2.6
D5	skin shadow L*=25	83.3	7.8	25.3	31.9	16.9	14.6	14.4	10.9
E5	skin shadow L*=11	82.0	6.1	15.8	20.4	16.9	16.8	10.5	14.6
F5	Max Black	100.0	0.3	6.1	6.3	0.4	0.5	-1.5	-1.3
Summary Results		I*Color	I*tone	 AARDENBURG IMAGING & ARCHIVES					
Average Score for all patches		75.4	86.4						
Average Score for the Worst 10% (3 lowest scoring patches)		32.0	77.9						

73.6_{color} / 85.4_{tone}



Original Print Colors
(measured before light exposure)




Colors after 240 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

240 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	67.1	9.2	36.5	43.5	13.2	11.4	10.5	4.7
B1	light Skin	46.1	11.9	65.1	69.9	14.7	14.2	12.6	1.7
C1	blue sky	79.7	6.9	51.5	56.1	-4.1	-5.1	-23.0	-17.8
D1	foliage	52.5	15.9	43.1	49.3	-12.5	-11.5	27.1	12.5
E1	blue flower	73.3	9.3	55.2	59.6	10.3	7.8	-27.0	-19.2
F1	bluish green	57.3	13.8	69.7	73.1	-30.2	-24.3	-1.4	-13.5
A2	orange	68.7	23.1	61.4	68.2	33.9	27.0	59.9	38.9
B2	purplish blue	84.5	9.2	37.7	41.4	12.1	7.0	-49.5	-42.9
C2	moderate red	81.4	11.7	46.1	52.1	49.2	45.5	14.1	4.8
D2	purple	89.5	6.3	28.3	33.0	23.9	22.1	-25.0	-21.3
E2	yellow green	62.6	25.7	71.3	76.3	-22.5	-22.5	62.2	37.0
F2	orange yellow	74.5	19.6	71.1	76.3	16.2	11.1	70.3	52.1
A3	blue	87.8	8.2	24.2	27.4	16.0	10.0	-55.5	-50.9
B3	green	51.6	25.9	54.5	61.5	-38.7	-33.8	32.5	8.0
C3	red	88.8	8.9	36.7	41.8	54.4	53.9	25.3	18.1
D3	yellow	94.6	6.7	78.9	83.0	6.0	1.1	88.7	86.6
E3	magenta	91.4	6.2	50.0	53.4	50.5	47.1	-19.6	-15.7
F3	cyan	91.0	5.5	51.3	55.2	-23.0	-23.8	-30.3	-26.5
A4	white	36.3	6.6	93.1	94.3	1.8	0.5	-3.5	2.9
B4	neutral 8	54.3	5.8	78.9	82.1	1.3	1.7	-3.5	1.3
C4	neutral 6.5	71.1	4.7	65.4	68.8	1.2	1.3	-4.8	-1.6
D4	neutral 5	97.1	5.0	49.8	54.7	1.3	1.8	-3.2	-2.7
E4	neutral 3.5	97.4	5.2	36.6	41.7	1.1	1.7	-2.9	-2.5
F4	black	96.0	4.3	21.8	26.0	1.0	1.0	-1.5	-2.4
A5	paper white	7.7	9.3	96.1	96.3	1.5	-0.3	-5.1	4.0
B5	skin highlight L*=89	84.3	3.5	85.7	88.1	11.6	10.4	6.3	4.0
C5	skin highlight L*=75	57.4	10.1	74.6	78.1	17.7	17.1	11.6	2.1
D5	skin shadow L*=25	82.2	8.7	25.3	32.7	16.9	14.6	14.4	10.6
E5	skin shadow L*=11	82.3	6.6	15.8	21.1	16.9	16.7	10.5	14.6
F5	Max Black	100.0	0.5	6.1	6.6	0.4	0.6	-1.5	-1.4
Summary Results		I*Color	I*tone	 AARDENBURG IMAGING & ARCHIVES					
Average Score for all patches		73.6	85.4						
Average Score for the Worst 10% (3 lowest scoring patches)		30.0	76.5						
		ΔE							

71.9_{color} / 84.5_{tone}



Original Print Colors
(measured before light exposure)



Colors after 260 Megalux-hours
light exposure

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*

260 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	dark Skin	65.7	9.8	36.5	44.0	13.2	11.7	10.5	4.4
B1	light Skin	43.2	12.6	65.1	70.2	14.7	14.5	12.6	1.1
C1	blue sky	79.7	7.1	51.5	56.3	-4.1	-4.8	-23.0	-17.8
D1	foliage	47.8	17.4	43.1	49.7	-12.5	-10.9	27.1	11.1
E1	blue flower	72.4	9.7	55.2	59.8	10.3	8.2	-27.0	-18.8
F1	bluish green	55.5	14.4	69.7	73.2	-30.2	-23.8	-1.4	-13.8
A2	orange	65.0	25.7	61.4	68.9	33.9	26.6	59.9	36.4
B2	purplish blue	83.5	9.8	37.7	41.8	12.1	7.0	-49.5	-42.3
C2	moderate red	80.7	12.3	46.1	52.7	49.2	45.5	14.1	4.4
D2	purple	86.9	7.5	28.3	33.9	23.9	21.9	-25.0	-20.4
E2	yellow green	57.5	29.1	71.3	76.5	-22.5	-22.2	62.2	33.6
F2	orange yellow	70.7	22.3	71.1	76.7	16.2	11.1	70.3	49.3
A3	blue	87.1	8.8	24.2	27.9	16.0	9.9	-55.5	-50.4
B3	green	48.0	27.7	54.5	61.8	-38.7	-33.0	32.5	6.3
C3	red	88.1	9.6	36.7	42.5	54.4	53.6	25.3	17.7
D3	yellow	93.1	7.9	78.9	83.3	6.0	0.6	88.7	84.8
E3	magenta	90.9	6.6	50.0	53.8	50.5	47.3	-19.6	-15.2
F3	cyan	91.3	5.6	51.3	55.4	-23.0	-23.2	-30.3	-26.5
A4	white	36.6	6.6	93.1	94.3	1.8	0.5	-3.5	2.9
B4	neutral 8	53.3	6.0	78.9	82.3	1.3	1.9	-3.5	1.4
C4	neutral 6.5	69.5	5.0	65.4	69.0	1.2	1.6	-4.8	-1.4
D4	neutral 5	94.0	5.4	49.8	55.1	1.3	2.2	-3.2	-2.7
E4	neutral 3.5	93.8	5.6	36.6	42.1	1.1	2.1	-2.9	-2.5
F4	black	95.0	4.7	21.8	26.4	1.0	1.4	-1.5	-2.4
A5	paper white	6.6	9.4	96.1	96.3	1.5	-0.3	-5.1	4.1
B5	skin highlight L*=89	81.5	3.9	85.7	88.3	11.6	10.6	6.3	3.6
C5	skin highlight L*=75	55.7	10.6	74.6	78.4	17.7	17.4	11.6	1.7
D5	skin shadow L*=25	81.6	9.3	25.3	33.4	16.9	14.7	14.4	10.4
E5	skin shadow L*=11	83.3	7.3	15.8	22.0	16.9	16.4	10.5	14.3
F5	Max Black	100.0	1.2	6.1	7.2	0.4	0.6	-1.5	-1.4

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

71.9

84.5


10.6

Average Score for the Worst 10%
(3 lowest scoring patches)


28.8

75.3

27.5



AARDENBURG IMAGING
& ARCHIVES



Original Print Colors
(measured before light exposure)



Test Complete

No further updates

*Canon iPF5000 Printer, Canon Lucia OEM ink,
Epson Exhibition Fiber 325gsm Paper*



AARDENBURG IMAGING
& ARCHIVES