

Aardenburg

144



IMAGING & ARCHIVES

Tested System:

ID#:295

Printer: Epson Stylus Pro 9800

Inks/Colorants: Epson OEM (K3 Ultrachrome)

Media: IJ Technologies Black Diamond Gloss Canvas

Coating(s): IJ Technologies Black Diamond Eclipse Top Coat

Sample #: AaI_20091008_SN009

Testing Status: 160 Megalux hours total light exposure

Testing Is ongoing, next update on approximately OCT 05, 2014

Conservation Display Rating (CDR)

Lower limit: 70 Megalux hours (for weakest 10% of the color patches)

Upper limit: 87 Megalux hours (for average of all the color patches)

Note: a CDR with narrow range (typically less than 2:1) indicates relatively even overall fading of the image. A wide range indicates faster fading in certain local colors/tones prior to general fading of most colors/tones in the entire image. Compare ratings for different systems directly and/or use the table on page 2 to estimate time (years) on display.

* Please read document AaI_2009_0118_TA-01.pdf, “An Overview of the AaI&A Conservation Display Ratings”, located on the Documents page of the AaI&A website for further explanation of the Conservation display ratings.

This report has been prepared for the exclusive use of members of Aardenburg Imaging & Archives. Members may share this information with other members, friends, colleagues, and individual clients. It may also be distributed to groups for educational purposes (classes, lectures, educational seminars. etc). However, all contents including but not limited to Conservation Display Ratings may not be posted to web sites and may not be reproduced or distributed for corporate research, marketing, or other promotional purposes without written permission from Aardenburg Imaging & Archives.

copyright ©2014

<http://www.aardenburg-imaging.com>

Aardenburg Imaging and Archives
Rev:8/14/14



About this Report

This report contains light fastness information about a sample test print produced by a specific digital printing system. “System” refers to all hardware, software, and materials used to make the finished print. The hardware, software, material components, and printmaker’s skills contribute to the final image quality and image permanence. The tested sample is made with current or recently discontinued stocks of commercially available products unless otherwise stated. Each sample has been prepared by Aardenburg Imaging & Archives or one of its members in accordance with customary print making practices unless otherwise noted. The sample may also contain additional finishing materials such as overcoats and laminates which are also noted when used. Finally, the sample has been tested under standardized conditions that are defined on the Sample Description page (see page 4). AaI&A makes every effort to ensure but cannot guarantee that the samples are properly identified and documented and that test results are accurate. For this reason, AaI&A also strives to test independently produced sample replicates in order to increase sampling confidence and to provide information on process variability. Please compare the results in this report to replicate test samples when the data become available.

Understanding this Report



The magnitude and visual appearance of fading depends not only on the chosen printing system but the chosen image as well. In other words, different images are comprised of different colors, and the fading relationships between those colors dictate how the image will look as it fades. The sample print in this test report was made by reproducing the digital image shown on the left. It contains 30 standard colors. 24 of the colors are colorimetrically matched to the Macbeth ColorChecker™ chart viewed under D50 illumination. The remaining six colors supplement the ColorChecker™ array with four additional skin tone colors, one patch for paper white, and another for maximum black. The additional colors also round out the distribution of CIELAB L* (lightness) values in the test target.

Information about the fading characteristics of the product is provided in three ways:

1) You can visually assess the fading. The target images reproduced in this report are digitally reconstructed from the spectrally measured color data rather than scanning or otherwise reproducing the physical print by conventional techniques. This method ensures a colorimetrically accurate representation of the print appearance as the print fades. A calibrated monitor is recommended to experience the best possible reproduction of the test sample appearance. The side-by-side “before and after” presentation of the target images simulates looking at a perfect copy of the unexposed original print along side the same print after light exposure. You can also use Adobe Reader’s full screen mode to cycle through the pages and “animate” the fading.

2) I* Color and tonal accuracy scores are reported. This report includes I* metric scores that compare the color and tonal relationships of the light exposed samples to the color and tonal relationships existing in the original print prior to light exposure. Perfect I* scores of 100% can be approached when no significant fading occurs. Average scores above 90% generally indicate excellent retention of original quality, 80% good, 70% fair, etc., but your conclusions may vary depending on your image quality requirements. I* color rates the retained color accuracy (hue and chroma) while I* tone rates the retained tonal accuracy (lightness and contrast). The score is on a percentile scale where 100% is a perfect match between the comparison image (e.g., “after” light exposure) and the reference image (e.g., “before” any light exposure). 0% I* color means no color accuracy is left. 0% I* tone means essentially no tonality remains and all image information content is lost. Negative I* values have significance as well and contribute to the average I* score when they occur. Negative I* color values mean false color has occurred, for example, when a skin tone turns green or a neutral gray becomes distinctly colorful. Negative I* tone scores mean visual contrast between colors has become inverted (i.e., like the tonal relationships in a photographic film negative). Serious image quality problems must arise before false colors and/or tones appear. For more information on the I* metric, please refer to the AaI&A web site.

3) Color changes are also reported using the classic color difference model, ΔE . Note that ΔE values lose perceptual scaling significance when they become large (e.g., > 15). Also, the ΔE equation does not unambiguously measure changes in image contrast. This limitation is generally not a problem for paints and textiles, but can be a serious oversight when evaluating photographic images. Properly tracking changes in image contrast was a major reason behind the development of the I* metric.

Table to Convert Megalux-hours of Light Exposure to estimated “Years on Display”												
Indoor Light Levels for Print Display		Multiply Mlux-hrs by	Megalux-hours in test									
Light Exposure	Description		10	20	30	40	50	60	70	80	90	100
≤ 10 Lux 24 hours per day	Interior rooms, storage areas, or hallways without windows, illuminated sparingly by artificial lighting	11.4	114	228	342	457	571	685	799	913	1027	1142
50 Lux 12 hours per day	“Museum Standard” display condition	4.6	46	91	137	183	228	274	325	365	411	457
120 Lux 12 hours per day “Kodak Display Years” (1)	Average home illumination level for photos is ~ 60 lux. 90% of all displayed photos do not exceed 120 lux (1).	1.9	19	38	57	76	95	114	133	152	171	190
228 Lux 12 hours per day	Relatively bright home or office. Note the simple 1:1 relationship between “years on display” and Mlux-hr values at this condition.	1.0	10	20	30	40	50	60	70	80	90	100
450 Lux 12 hours per day “WIR Display Years” (2) Also equals 500 lux for 11.8 hours per day	A bright home or commercial office building illumination level is 200-500 lux. Also, good illumination for color critical viewing and color matching tasks begins at about 500 lux.	0.5	5	10	15	20	25	30	35	41	46	51

Light levels commonly encountered in the real world fluctuate widely throughout indoor print display environments and produce large variations in how long it takes for artwork to acquire light-induced damage. Use this table as a guide to estimate how many “years on display” (denoted in red text) it takes to accumulate the light exposure test dosage. Review the test results to decide which Megalux-hour dose has caused fading to your level of concern (e.g., just noticeable, easily noticeable, objectionable, etc.). Then choose the print display description that best represents how your print is likely to be displayed. You may want to obtain a lux meter and make some measurements in your own display environment!

Note that as the years of display time increase, light-induced fading can be eclipsed by other serious aging mechanisms such as fading and/or staining caused by heat, humidity, and air pollutants. Mould damage can also occur at high humidity. Even when colorants remain water fast, direct contact with liquids may result in physical deformation and staining of the substrate. Also, temperature and especially humidity cycling can cause physical cracks and/or flaking, etc. Handling damage such as scratching, abrasion, tears and creases, and catastrophic damage by smoke, fire, flood, etc., also degrade print quality over time. Thus, as illumination levels are reduced other forms of degradation take on greater proportion of risk and may appear in shorter time intervals.

(1) Eastman Kodak cited this exposure condition with a 90% confidence limit as a rationale for estimating print fading times of traditional color photo materials in typical home display environments. For light fading claims regarding its newer line of pigment-based inkjet printers, Kodak adopted the higher level of 450lux/12 hours per day which is also used by Wilhelm Imaging Research, Inc. (See below).

(2) Wilhelm Imaging Research (WIR) standardized its light fastness ratings on 450 lux for 12 hours per day in order to estimate the years on display necessary to reach “easily noticeable” fading. This average daily light exposure dose (at 75°F/60%RH assumed temperature and humidity levels) used in conjunction with WIR’s visually weighted densitometric endpoint criteria set V3.0 became a de facto industry standard during the first decade of the 21st century in the absence of a published International Standards Organization (ISO) test standard. However, the WIR V3.0 visual criteria set used to predict “easily noticeable fade” was designed for traditional 20th century silver–halide color photofinishing processes. It is not well suited to the evaluation of modern digital media. Nevertheless, the WIR assumed daily light exposure dose is one of many commonly encountered light exposure conditions existing within the range of real world picture display locations.

Sample Description

Sample # AaI_20091008_SN009 **Batch #:** I1a
Printer: Epson Stylus Pro 9800
Ink: Epson OEM (K3 Ultrachrome)
Media: IJ Technologies Black Diamond Gloss Canvas
Coating(s): IJ Technologies Black Diamond Eclipse Top Coat

Test Print Prepared by: AaI&A member
Printed: October 8, 2009
Initial Print colors measured September 19, 2010
Test Started: September 19, 2010

Test Image: AaI_StandardColorSet(v2)forSRGB.tif
RIP?Driver settings: Colorbyte ImagePrint v6.1, 1440 8 pass high speed

Media Setting canvas, 1440 8 pass high speed, KCMYCM Pigment, (PK photo black used)

Profile: n.a. **Rendering** n.a.
Profile type: custom

Paper White Color (UV-included versus UV-excluded)

Optical Brighteners Present? <i>no</i>	L*		a*		b*	
Media Whitepoint Color	UV inc	UV exc	UV inc	UV exc	UV inc	UV exc
	95.9	96.3	-0.3	-0.3	1.4	1.2
	<i>UV-inc/UV-exc ΔL^*, Δa^*, Δb^* respectively</i>					
	0.4		0.1		0.2	
	<i>Calculated differences, especially for Δb^*, indicate the role and magnitude of fluorescence on original paper color</i>					
Maximum Printed Black	L*	a*	b*	Optical Density (Dmax)		
	15.1	-3.0	1.0	1.72		

Light source: Phillips Colortone F40T12/C50 – 5000°K full spectrum fluorescent. Color rendering Index (CRI) =92), soda lime glass filtered
Light Exposure Cycle: 8 hours on, 4 hours off, twice per 24 hours
CIELAB measurements: D50 2° observer, Xrite Gretag/Macbeth Spectrolino/Spectroscan

Average Illuminance during “on” cycle: 11254 Lux
Average Temperature: 23.3°C over full test duration, 24.7°C during light exposure.
Average Relative humidity: 56.7%RH over full test duration, 56.5%RH during light exposure.

Notes/Comments:


*Low levels of optical brightener (OBA) are present in the canvas weave, but none has been added to the coating. Hence, no media whitepoint fluorescence occurs.

Compare this sample to sample # AaI_20091008_SN007 which was made with the same printer, and same ink and canvas batches, only AaI_20091008_SN007 was not coated.



Notes/Comments: continued...

Graphs:

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Values:

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	100.0	1.1	41.2	42.3	11.0	10.9	12.4	12.1
B1	Light Skin	98.7	1.1	65.9	66.8	14.9	14.3	16.7	16.1
C1	Blue sky	100.0	0.9	51.9	52.7	-5.9	-6.1	-17.6	-17.6
D1	Foliage	100.0	1.0	45.7	46.6	-11.9	-12.1	19.7	19.3
E1	blue flower	98.9	1.2	56.2	57.2	6.3	5.7	-21.0	-20.5
F1	bluish green	98.4	1.2	70.0	70.7	-32.3	-32.2	2.2	1.2
A1	orange	99.3	1.0	62.5	63.0	31.8	31.1	48.6	48.1
B2	purplish blue	98.0	1.5	42.8	43.6	7.0	6.2	-38.8	-37.9
C2	moderate red	100.0	0.3	51.8	52.1	42.4	42.5	12.8	12.8
D2	purple	100.0	0.8	35.1	35.8	18.7	18.6	-17.9	-17.5
E2	yellow green	99.6	1.0	72.2	72.9	-23.0	-23.4	51.6	51.0
F2	orange yellow	98.9	1.3	71.0	71.6	16.0	15.0	59.9	59.2
A3	blue	98.9	1.1	33.9	34.5	9.5	8.8	-41.3	-40.7
B3	green	99.8	0.9	56.7	57.4	-34.7	-35.1	29.6	29.2
C3	red	100.0	0.5	43.6	43.9	47.7	47.5	22.8	22.3
D3	yellow	99.3	1.1	79.9	80.3	1.9	1.0	72.7	72.2
E3	magenta	98.2	1.4	52.3	52.7	45.6	44.7	-13.2	-12.1
F3	cyan	100.0	1.0	53.7	54.7	-22.2	-22.4	-21.5	-21.6
A4	white	99.5	0.6	92.8	93.1	-0.7	-0.9	2.7	2.2
B4	neutral 8	99.0	0.8	79.0	79.6	-1.8	-2.3	2.5	2.1
C4	neutral 6.5	100.0	1.0	66.9	67.8	-2.1	-2.5	1.7	1.4
D4	neutral 5	100.0	1.0	53.0	54.0	-1.5	-1.8	2.7	2.5
E4	neutral 3.5	100.0	0.9	40.5	41.4	-1.2	-1.4	1.6	1.5
F4	black	100.0	0.8	27.3	28.1	-1.4	-1.5	2.0	1.9
A5	paper white	100.0	0.5	95.7	96.0	-0.2	-0.2	1.2	0.8
B5	Skin highlight L*=88	96.9	1.1	85.4	85.7	10.5	9.9	14.2	13.3
C5	Skin highlight L* =75	97.9	1.2	73.7	74.4	16.9	16.1	18.6	18.1
D5	Skin shadow L*=28	100.0	0.9	29.6	30.5	12.2	12.3	12.7	12.6
E5	Skin shadow L*=13	100.0	0.6	21.3	21.9	10.4	10.4	10.1	10.0
F5	Maximum Black	100.0	0.9	15.1	16.0	-3.0	-2.9	1.0	1.2
Summary Results		I* Color	I* tone	ΔE	10 Megalux hours				
Average Score for all patches		99.4	97.5	1.0					
Worst 10% (3 lowest scoring patches)		97.6	95.6	1.4					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	99.9	1.5	41.2	42.7	11.0	10.9	12.4	11.8
B1	Light Skin	96.3	1.8	65.9	67.1	14.9	14.2	16.7	15.5
C1	Blue sky	100.0	1.2	51.9	53.1	-5.9	-6.1	-17.6	-17.6
D1	Foliage	98.3	1.5	45.7	46.9	-11.9	-12.1	19.7	18.8
E1	blue flower	98.4	1.6	56.2	57.6	6.3	5.7	-21.0	-20.4
F1	bluish green	95.9	2.1	70.0	71.0	-32.3	-31.9	2.2	0.4
A1	orange	98.8	1.4	62.5	63.3	31.8	30.9	48.6	47.8
B2	purplish blue	96.9	2.3	42.8	44.3	7.0	6.1	-38.8	-37.4
C2	moderate red	100.0	0.8	51.8	52.4	42.4	42.1	12.8	12.5
D2	purple	100.0	0.9	35.1	35.9	18.7	18.7	-17.9	-17.5
E2	yellow green	98.1	1.9	72.2	73.2	-23.0	-23.6	51.6	50.2
F2	orange yellow	97.9	2.0	71.0	71.9	16.0	14.7	59.9	58.7
A3	blue	98.1	1.5	33.9	34.7	9.5	8.6	-41.3	-40.4
B3	green	98.2	1.7	56.7	57.7	-34.7	-35.3	29.6	28.4
C3	red	99.7	0.8	43.6	44.1	47.7	47.6	22.8	22.1
D3	yellow	98.4	1.8	79.9	80.6	1.9	0.7	72.7	71.7
E3	magenta	97.0	2.1	52.3	53.1	45.6	44.7	-13.2	-11.5
F3	cyan	100.0	1.4	53.7	55.1	-22.2	-22.2	-21.5	-21.8
A4	white	97.3	0.8	92.8	93.2	-0.7	-0.9	2.7	2.0
B4	neutral 8	96.3	1.2	79.0	79.9	-1.8	-2.3	2.5	1.7
C4	neutral 6.5	98.6	1.5	66.9	68.2	-2.1	-2.4	1.7	1.1
D4	neutral 5	100.0	1.5	53.0	54.5	-1.5	-1.7	2.7	2.2
E4	neutral 3.5	100.0	1.3	40.5	41.8	-1.2	-1.3	1.6	1.4
F4	black	100.0	1.0	27.3	28.3	-1.4	-1.5	2.0	1.8
A5	paper white	100.0	0.6	95.7	96.1	-0.2	-0.3	1.2	0.7
B5	Skin highlight L*=88	92.9	1.9	85.4	86.2	10.5	9.6	14.2	12.7
C5	Skin highlight L* =75	95.4	2.0	73.7	74.8	16.9	15.9	18.6	17.3
D5	Skin shadow L*=28	100.0	1.3	29.6	30.9	12.2	12.2	12.7	12.5
E5	Skin shadow L*=13	100.0	1.1	21.3	22.3	10.4	10.4	10.1	10.2
F5	Maximum Black	100.0	1.4	15.1	16.5	-3.0	-2.8	1.0	1.2
Summary Results		I* Color	I* tone	ΔE	20 Megalux hours				
Average Score for all patches		98.4	96.5	1.5					
Worst 10% (3 lowest scoring patches)		94.7	94.5	2.1					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	99.1	1.9	41.2	43.0	11.0	11.0	12.4	11.7
B1	Light Skin	94.0	2.3	65.9	67.4	14.9	14.3	16.7	15.0
C1	Blue sky	100.0	1.5	51.9	53.3	-5.9	-5.9	-17.6	-17.8
D1	Foliage	95.9	2.0	45.7	47.1	-11.9	-12.0	19.7	18.2
E1	blue flower	98.3	1.9	56.2	57.9	6.3	5.9	-21.0	-20.2
F1	bluish green	93.0	3.0	70.0	71.2	-32.3	-31.7	2.2	-0.5
A1	orange	97.6	2.1	62.5	63.4	31.8	30.8	48.6	47.1
B2	purplish blue	96.4	2.5	42.8	44.5	7.0	6.0	-38.8	-37.2
C2	moderate red	99.7	1.0	51.8	52.6	42.4	42.2	12.8	12.2
D2	purple	100.0	1.1	35.1	36.2	18.7	18.8	-17.9	-17.5
E2	yellow green	96.4	2.8	72.2	73.4	-23.0	-23.7	51.6	49.2
F2	orange yellow	96.8	2.7	71.0	72.2	16.0	14.4	59.9	58.0
A3	blue	97.8	1.8	33.9	34.9	9.5	8.6	-41.3	-40.2
B3	green	96.8	2.4	56.7	58.0	-34.7	-35.4	29.6	27.7
C3	red	99.3	1.1	43.6	44.3	47.7	47.7	22.8	21.9
D3	yellow	97.4	2.6	79.9	80.9	1.9	0.3	72.7	70.9
E3	magenta	95.7	2.8	52.3	53.4	45.6	44.5	-13.2	-10.9
F3	cyan	99.6	1.7	53.7	55.3	-22.2	-22.1	-21.5	-22.1
A4	white	96.1	0.9	92.8	93.1	-0.7	-1.0	2.7	1.9
B4	neutral 8	93.9	1.5	79.0	80.0	-1.8	-2.3	2.5	1.5
C4	neutral 6.5	97.8	1.7	66.9	68.5	-2.1	-2.4	1.7	1.0
D4	neutral 5	99.8	1.8	53.0	54.8	-1.5	-1.6	2.7	2.1
E4	neutral 3.5	100.0	1.7	40.5	42.2	-1.2	-1.2	1.6	1.4
F4	black	100.0	1.4	27.3	28.7	-1.4	-1.4	2.0	1.8
A5	paper white	100.0	0.5	95.7	96.0	-0.2	-0.3	1.2	0.8
B5	Skin highlight L*=88	89.4	2.5	85.4	86.3	10.5	9.6	14.2	12.0
C5	Skin highlight L* =75	93.4	2.5	73.7	75.0	16.9	15.8	18.6	16.8
D5	Skin shadow L*=28	100.0	1.7	29.6	31.3	12.2	12.3	12.7	12.4
E5	Skin shadow L*=13	100.0	1.2	21.3	22.5	10.4	10.4	10.1	10.0
F5	Maximum Black	97.4	2.2	15.1	17.1	-3.0	-2.5	1.0	1.6
Summary Results		I* Color	I* tone	ΔE	30 Megalux hours				
Average Score for all patches		97.4	95.8	1.9					
Worst 10% (3 lowest scoring patches)		91.9	94.0	2.9					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	98.1	2.0	41.2	43.1	11.0	11.1	12.4	11.5
B1	Light Skin	91.6	2.9	65.9	67.6	14.9	14.3	16.7	14.4
C1	Blue sky	100.0	1.8	51.9	53.6	-5.9	-5.7	-17.6	-17.9
D1	Foliage	94.1	2.5	45.7	47.4	-11.9	-11.8	19.7	17.8
E1	blue flower	97.3	2.3	56.2	58.2	6.3	5.9	-21.0	-20.0
F1	bluish green	90.3	3.9	70.0	71.3	-32.3	-31.4	2.2	-1.3
A1	orange	96.8	2.6	62.5	63.6	31.8	30.8	48.6	46.5
B2	purplish blue	95.0	3.1	42.8	44.8	7.0	6.0	-38.8	-36.6
C2	moderate red	99.3	1.2	51.8	52.8	42.4	42.1	12.8	12.1
D2	purple	100.0	1.3	35.1	36.3	18.7	18.8	-17.9	-17.4
E2	yellow green	94.7	3.8	72.2	73.5	-23.0	-23.8	51.6	48.2
F2	orange yellow	95.3	3.7	71.0	72.3	16.0	14.3	59.9	56.9
A3	blue	96.6	2.4	33.9	35.2	9.5	8.5	-41.3	-39.6
B3	green	95.2	3.1	56.7	58.1	-34.7	-35.4	29.6	27.0
C3	red	98.8	1.3	43.6	44.4	47.7	47.6	22.8	21.7
D3	yellow	96.4	3.3	79.9	81.0	1.9	0.1	72.7	70.2
E3	magenta	94.1	3.6	52.3	53.7	45.6	44.3	-13.2	-10.2
F3	cyan	98.2	2.2	53.7	55.6	-22.2	-21.6	-21.5	-22.3
A4	white	97.1	0.9	92.8	93.2	-0.7	-1.0	2.7	2.0
B4	neutral 8	92.3	1.6	79.0	80.1	-1.8	-2.2	2.5	1.3
C4	neutral 6.5	96.6	2.0	66.9	68.7	-2.1	-2.2	1.7	0.9
D4	neutral 5	98.5	2.2	53.0	55.1	-1.5	-1.5	2.7	2.0
E4	neutral 3.5	100.0	1.9	40.5	42.4	-1.2	-1.1	1.6	1.3
F4	black	100.0	1.7	27.3	29.0	-1.4	-1.2	2.0	2.0
A5	paper white	100.0	0.4	95.7	96.0	-0.2	-0.3	1.2	1.0
B5	Skin highlight L*=88	86.8	3.0	85.4	86.4	10.5	9.5	14.2	11.5
C5	Skin highlight L* =75	90.5	3.3	73.7	75.3	16.9	15.8	18.6	16.0
D5	Skin shadow L*=28	100.0	1.7	29.6	31.3	12.2	12.3	12.7	12.4
E5	Skin shadow L*=13	100.0	1.4	21.3	22.7	10.4	10.4	10.1	9.9
F5	Maximum Black	100.0	1.5	15.1	16.5	-3.0	-3.0	1.0	1.3
Summary Results		I* Color	I* tone	ΔE	40 Megalux hours				
Average Score for all patches		96.5	95.2	2.3					
Worst 10% (3 lowest scoring patches)		89.2	93.2	3.8					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	96.0	2.4	41.2	43.4	11.0	11.3	12.4	11.2
B1	Light Skin	88.2	3.7	65.9	67.8	14.9	14.5	16.7	13.6
C1	Blue sky	98.8	2.1	51.9	53.9	-5.9	-5.4	-17.6	-18.1
D1	Foliage	90.4	3.3	45.7	47.5	-11.9	-11.7	19.7	17.0
E1	blue flower	98.2	2.3	56.2	58.4	6.3	6.1	-21.0	-20.1
F1	bluish green	86.7	5.0	70.0	71.5	-32.3	-31.2	2.2	-2.5
A1	orange	95.6	3.3	62.5	63.8	31.8	30.6	48.6	45.8
B2	purplish blue	95.0	3.1	42.8	44.7	7.0	5.9	-38.8	-36.6
C2	moderate red	97.2	2.2	51.8	53.2	42.4	41.4	12.8	11.4
D2	purple	100.0	1.5	35.1	36.5	18.7	19.0	-17.9	-17.4
E2	yellow green	93.0	4.7	72.2	73.7	-23.0	-24.0	51.6	47.3
F2	orange yellow	93.7	4.6	71.0	72.5	16.0	14.1	59.9	55.9
A3	blue	96.6	2.3	33.9	35.1	9.5	8.3	-41.3	-39.8
B3	green	92.8	4.2	56.7	58.4	-34.7	-35.1	29.6	25.8
C3	red	98.5	1.5	43.6	44.3	47.7	47.9	22.8	21.5
D3	yellow	94.8	4.4	79.9	81.1	1.9	-0.2	72.7	69.0
E3	magenta	93.2	4.0	52.3	53.8	45.6	44.2	-13.2	-9.7
F3	cyan	96.8	2.5	53.7	55.7	-22.2	-21.4	-21.5	-22.7
A4	white	94.8	1.1	92.8	93.2	-0.7	-1.0	2.7	1.7
B4	neutral 8	88.0	1.9	79.0	80.1	-1.8	-2.2	2.5	0.9
C4	neutral 6.5	91.8	2.3	66.9	68.8	-2.1	-2.2	1.7	0.4
D4	neutral 5	94.8	2.4	53.0	55.2	-1.5	-1.3	2.7	1.7
E4	neutral 3.5	99.9	2.0	40.5	42.5	-1.2	-1.0	1.6	1.2
F4	black	100.0	1.7	27.3	29.0	-1.4	-1.2	2.0	1.8
A5	paper white	100.0	0.3	95.7	95.8	-0.2	-0.3	1.2	0.9
B5	Skin highlight L*=88	82.2	3.8	85.4	86.3	10.5	9.5	14.2	10.7
C5	Skin highlight L* =75	87.6	4.0	73.7	75.3	16.9	15.8	18.6	15.2
D5	Skin shadow L*=28	100.0	1.7	29.6	31.3	12.2	12.4	12.7	12.3
E5	Skin shadow L*=13	100.0	1.4	21.3	22.7	10.4	10.4	10.1	10.1
F5	Maximum Black	100.0	2.0	15.1	17.0	-3.0	-2.8	1.0	1.3
Summary Results		I* Color	I* tone	ΔE	50 Megalux hours				
Average Score for all patches		94.8	94.6	2.7					
Worst 10% (3 lowest scoring patches)		85.5	92.3	4.8					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	95.2	2.9	41.2	43.8	11.0	11.3	12.4	11.1
B1	Light Skin	85.8	4.3	65.9	68.1	14.9	14.4	16.7	13.1
C1	Blue sky	97.8	2.6	51.9	54.3	-5.9	-5.2	-17.6	-18.2
D1	Foliage	89.2	3.7	45.7	47.9	-11.9	-11.5	19.7	16.7
E1	blue flower	97.0	2.9	56.2	58.8	6.3	6.2	-21.0	-19.8
F1	bluish green	84.3	5.8	70.0	71.7	-32.3	-30.7	2.2	-3.1
A1	orange	94.3	4.1	62.5	64.0	31.8	30.5	48.6	45.0
B2	purplish blue	93.5	4.0	42.8	45.4	7.0	6.0	-38.8	-35.9
C2	moderate red	98.2	1.8	51.8	53.1	42.4	42.3	12.8	11.6
D2	purple	97.8	2.3	35.1	37.1	18.7	19.1	-17.9	-16.9
E2	yellow green	91.2	5.8	72.2	74.0	-23.0	-23.7	51.6	46.2
F2	orange yellow	92.7	5.3	71.0	72.7	16.0	13.9	59.9	55.3
A3	blue	95.3	3.1	33.9	35.8	9.5	8.3	-41.3	-39.1
B3	green	91.9	4.6	56.7	58.7	-34.7	-35.3	29.6	25.4
C3	red	97.8	2.0	43.6	44.8	47.7	47.7	22.8	21.1
D3	yellow	93.6	5.4	79.9	81.5	1.9	-0.4	72.7	68.1
E3	magenta	92.8	4.2	52.3	53.9	45.6	44.6	-13.2	-9.4
F3	cyan	96.1	3.0	53.7	56.2	-22.2	-21.3	-21.5	-22.9
A4	white	94.1	1.1	92.8	93.2	-0.7	-0.9	2.7	1.7
B4	neutral 8	87.7	2.1	79.0	80.4	-1.8	-2.1	2.5	0.8
C4	neutral 6.5	91.1	2.7	66.9	69.2	-2.1	-2.0	1.7	0.4
D4	neutral 5	93.4	3.0	53.0	55.8	-1.5	-1.2	2.7	1.6
E4	neutral 3.5	99.1	2.6	40.5	43.0	-1.2	-0.8	1.6	1.2
F4	black	100.0	2.4	27.3	29.7	-1.4	-1.1	2.0	1.9
A5	paper white	100.0	0.2	95.7	95.9	-0.2	-0.3	1.2	1.1
B5	Skin highlight L*=88	80.3	4.2	85.4	86.6	10.5	9.4	14.2	10.4
C5	Skin highlight L* =75	85.5	4.6	73.7	75.8	16.9	15.7	18.6	14.6
D5	Skin shadow L*=28	99.1	2.5	29.6	32.1	12.2	12.4	12.7	12.0
E5	Skin shadow L*=13	100.0	2.1	21.3	23.4	10.4	10.3	10.1	9.7
F5	Maximum Black	95.3	3.6	15.1	18.6	-3.0	-2.3	1.0	1.6
Summary Results		I* Color	I* tone	ΔE	60 Megalux hours				
Average Score for all patches		93.7	93.1	3.3					
Worst 10% (3 lowest scoring patches)		83.4	89.4	5.6					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	93.1	3.1	41.2	43.9	11.0	11.4	12.4	10.8
B1	Light Skin	82.8	4.9	65.9	68.2	14.9	14.5	16.7	12.4
C1	Blue sky	96.1	2.7	51.9	54.3	-5.9	-5.1	-17.6	-18.5
D1	Foliage	86.4	4.3	45.7	47.9	-11.9	-11.4	19.7	16.1
E1	blue flower	97.7	3.0	56.2	59.1	6.3	6.3	-21.0	-20.0
F1	bluish green	81.4	6.8	70.0	71.9	-32.3	-30.4	2.2	-4.0
A1	orange	93.2	4.7	62.5	64.1	31.8	30.5	48.6	44.4
B2	purplish blue	93.8	3.8	42.8	45.3	7.0	5.9	-38.8	-36.1
C2	moderate red	97.8	1.9	51.8	53.0	42.4	43.3	12.8	11.6
D2	purple	99.2	1.9	35.1	36.9	18.7	19.3	-17.9	-17.4
E2	yellow green	89.7	6.7	72.2	74.2	-23.0	-23.8	51.6	45.3
F2	orange yellow	91.3	6.2	71.0	73.0	16.0	13.8	59.9	54.4
A3	blue	95.6	3.0	33.9	35.8	9.5	8.4	-41.3	-39.2
B3	green	90.3	5.4	56.7	58.9	-34.7	-35.3	29.6	24.7
C3	red	97.2	2.4	43.6	45.0	47.7	47.8	22.8	20.8
D3	yellow	92.5	6.2	79.9	81.5	1.9	-0.6	72.7	67.3
E3	magenta	92.0	4.7	52.3	54.2	45.6	44.4	-13.2	-9.1
F3	cyan	94.1	3.5	53.7	56.3	-22.2	-20.8	-21.5	-23.3
A4	white	92.1	1.3	92.8	93.2	-0.7	-0.9	2.7	1.5
B4	neutral 8	83.7	2.5	79.0	80.4	-1.8	-2.0	2.5	0.4
C4	neutral 6.5	85.9	3.1	66.9	69.3	-2.1	-1.9	1.7	-0.1
D4	neutral 5	89.5	3.2	53.0	55.9	-1.5	-1.1	2.7	1.2
E4	neutral 3.5	96.9	2.8	40.5	43.2	-1.2	-0.6	1.6	1.0
F4	black	100.0	2.4	27.3	29.7	-1.4	-1.0	2.0	1.9
A5	paper white	100.0	0.2	95.7	95.9	-0.2	-0.3	1.2	1.1
B5	Skin highlight L*=88	76.0	4.9	85.4	86.7	10.5	9.4	14.2	9.6
C5	Skin highlight L* =75	82.1	5.4	73.7	75.8	16.9	15.8	18.6	13.7
D5	Skin shadow L*=28	98.6	2.6	29.6	32.1	12.2	12.5	12.7	12.0
E5	Skin shadow L*=13	100.0	2.1	21.3	23.4	10.4	10.5	10.1	9.9
F5	Maximum Black	96.8	3.0	15.1	17.9	-3.0	-2.4	1.0	1.5
Summary Results		I* Color	I* tone	ΔE	70 Megalux hours				
Average Score for all patches		92.2	93.1	3.6					
Worst 10% (3 lowest scoring patches)		79.8	90.3	6.5					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	91.7	3.4	41.2	44.0	11.0	11.6	12.4	10.6
B1	Light Skin	80.0	5.6	65.9	68.5	14.9	14.7	16.7	11.8
C1	Blue sky	94.3	3.1	51.9	54.5	-5.9	-4.8	-17.6	-18.7
D1	Foliage	83.3	5.0	45.7	48.1	-11.9	-11.3	19.7	15.4
E1	blue flower	97.7	3.1	56.2	59.2	6.3	6.5	-21.0	-20.0
F1	bluish green	78.6	7.7	70.0	72.0	-32.3	-30.0	2.2	-4.9
A1	orange	92.0	5.4	62.5	64.2	31.8	30.4	48.6	43.7
B2	purplish blue	93.2	4.2	42.8	45.6	7.0	6.1	-38.8	-35.8
C2	moderate red	96.9	2.4	51.8	53.3	42.4	42.9	12.8	11.0
D2	purple	98.4	2.3	35.1	37.2	18.7	19.5	-17.9	-17.3
E2	yellow green	87.8	7.7	72.2	74.4	-23.0	-23.8	51.6	44.2
F2	orange yellow	90.0	7.0	71.0	73.1	16.0	13.8	59.9	53.6
A3	blue	95.2	3.3	33.9	36.0	9.5	8.4	-41.3	-39.0
B3	green	88.3	6.3	56.7	59.0	-34.7	-35.2	29.6	23.8
C3	red	96.6	2.7	43.6	45.1	47.7	47.9	22.8	20.5
D3	yellow	91.3	7.0	79.9	81.7	1.9	-0.8	72.7	66.5
E3	magenta	90.9	5.2	52.3	54.4	45.6	44.3	-13.2	-8.6
F3	cyan	93.1	3.8	53.7	56.4	-22.2	-20.7	-21.5	-23.6
A4	white	91.6	1.4	92.8	93.2	-0.7	-0.9	2.7	1.4
B4	neutral 8	81.7	2.7	79.0	80.5	-1.8	-2.0	2.5	0.2
C4	neutral 6.5	84.0	3.3	66.9	69.5	-2.1	-1.8	1.7	-0.3
D4	neutral 5	87.1	3.5	53.0	56.1	-1.5	-0.9	2.7	1.0
E4	neutral 3.5	95.3	3.0	40.5	43.3	-1.2	-0.6	1.6	0.9
F4	black	99.6	2.6	27.3	29.8	-1.4	-0.9	2.0	1.8
A5	paper white	100.0	0.3	95.7	96.0	-0.2	-0.3	1.2	1.2
B5	Skin highlight L*=88	73.5	5.4	85.4	86.8	10.5	9.5	14.2	9.1
C5	Skin highlight L* =75	79.8	6.1	73.7	76.1	16.9	15.9	18.6	13.1
D5	Skin shadow L*=28	97.5	2.7	29.6	32.2	12.2	12.6	12.7	11.8
E5	Skin shadow L*=13	100.0	2.1	21.3	23.4	10.4	10.5	10.1	9.8
F5	Maximum Black	97.0	3.2	15.1	18.2	-3.0	-2.4	1.0	1.5
Summary Results		I* Color	I* tone	ΔE	80 Megalux hours				
Average Score for all patches		90.9	92.9	4.0					
Worst 10% (3 lowest scoring patches)		77.3	89.9	7.5					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	90.1	3.6	41.2	44.2	11.0	11.8	12.4	10.4
B1	Light Skin	77.4	6.1	65.9	68.6	14.9	14.9	16.7	11.2
C1	Blue sky	92.2	3.5	51.9	54.8	-5.9	-4.5	-17.6	-19.0
D1	Foliage	80.8	5.5	45.7	48.3	-11.9	-11.0	19.7	14.8
E1	blue flower	97.6	3.2	56.2	59.2	6.3	6.7	-21.0	-20.1
F1	bluish green	75.5	8.7	70.0	72.1	-32.3	-29.7	2.2	-5.8
A1	orange	90.6	6.2	62.5	64.3	31.8	30.5	48.6	42.8
B2	purplish blue	92.9	4.4	42.8	45.8	7.0	6.1	-38.8	-35.7
C2	moderate red	96.4	2.6	51.8	53.4	42.4	43.0	12.8	10.8
D2	purple	97.0	2.8	35.1	37.6	18.7	19.6	-17.9	-17.0
E2	yellow green	85.8	8.8	72.2	74.5	-23.0	-23.7	51.6	43.1
F2	orange yellow	88.6	7.8	71.0	73.1	16.0	13.8	59.9	52.7
A3	blue	95.1	3.3	33.9	36.0	9.5	8.2	-41.3	-39.0
B3	green	86.0	7.3	56.7	59.2	-34.7	-34.8	29.6	22.7
C3	red	96.1	2.9	43.6	45.1	47.7	48.1	22.8	20.2
D3	yellow	89.7	8.2	79.9	81.8	1.9	-0.8	72.7	65.2
E3	magenta	90.6	5.3	52.3	54.2	45.6	44.7	-13.2	-8.3
F3	cyan	91.7	4.2	53.7	56.6	-22.2	-20.4	-21.5	-24.0
A4	white	91.3	1.4	92.8	93.1	-0.7	-0.8	2.7	1.4
B4	neutral 8	80.0	2.8	79.0	80.5	-1.8	-1.9	2.5	0.1
C4	neutral 6.5	81.0	3.5	66.9	69.6	-2.1	-1.7	1.7	-0.6
D4	neutral 5	84.1	3.7	53.0	56.1	-1.5	-0.8	2.7	0.8
E4	neutral 3.5	92.5	3.0	40.5	43.3	-1.2	-0.4	1.6	0.6
F4	black	99.6	2.5	27.3	29.7	-1.4	-0.9	2.0	1.7
A5	paper white	100.0	0.3	95.7	95.9	-0.2	-0.4	1.2	1.4
B5	Skin highlight L*=88	70.7	5.8	85.4	86.7	10.5	9.5	14.2	8.6
C5	Skin highlight L* =75	77.0	6.7	73.7	76.1	16.9	15.9	18.6	12.4
D5	Skin shadow L*=28	96.7	2.8	29.6	32.2	12.2	12.7	12.7	11.7
E5	Skin shadow L*=13	100.0	2.3	21.3	23.5	10.4	10.7	10.1	9.7
F5	Maximum Black	96.7	3.2	15.1	18.2	-3.0	-2.4	1.0	1.5
Summary Results		I* Color	I* tone	ΔE	90 Megalux hours				
Average Score for all patches		89.4	92.4	4.4					
Worst 10% (3 lowest scoring patches)		74.4	88.7	8.6					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	88.1	3.9	41.2	44.3	11.0	11.9	12.4	10.0
B1	Light Skin	74.6	6.8	65.9	68.7	14.9	15.0	16.7	10.5
C1	Blue sky	90.9	3.6	51.9	54.8	-5.9	-4.5	-17.6	-19.3
D1	Foliage	78.2	6.1	45.7	48.3	-11.9	-11.0	19.7	14.2
E1	blue flower	97.3	3.5	56.2	59.5	6.3	6.8	-21.0	-20.0
F1	bluish green	72.6	9.6	70.0	72.4	-32.3	-29.3	2.2	-6.7
A1	orange	89.7	6.8	62.5	64.5	31.8	30.5	48.6	42.3
B2	purplish blue	92.4	4.7	42.8	45.9	7.0	6.2	-38.8	-35.4
C2	moderate red	95.6	3.0	51.8	53.5	42.4	43.1	12.8	10.5
D2	purple	98.4	2.5	35.1	37.4	18.7	19.6	-17.9	-17.5
E2	yellow green	84.0	9.9	72.2	74.7	-23.0	-23.7	51.6	42.1
F2	orange yellow	87.0	8.9	71.0	73.4	16.0	13.8	59.9	51.6
A3	blue	94.9	3.5	33.9	36.2	9.5	8.3	-41.3	-38.9
B3	green	84.2	8.2	56.7	59.4	-34.7	-34.8	29.6	21.9
C3	red	95.6	3.2	43.6	45.3	47.7	48.2	22.8	20.0
D3	yellow	88.4	9.2	79.9	81.9	1.9	-0.9	72.7	64.2
E3	magenta	89.1	6.2	52.3	54.8	45.6	44.3	-13.2	-7.7
F3	cyan	90.3	4.7	53.7	56.9	-22.2	-20.0	-21.5	-24.2
A4	white	90.5	1.5	92.8	93.2	-0.7	-0.8	2.7	1.3
B4	neutral 8	77.5	3.1	79.0	80.7	-1.8	-1.8	2.5	-0.2
C4	neutral 6.5	76.9	3.9	66.9	69.7	-2.1	-1.6	1.7	-0.9
D4	neutral 5	80.7	4.1	53.0	56.3	-1.5	-0.6	2.7	0.5
E4	neutral 3.5	90.6	3.4	40.5	43.6	-1.2	-0.3	1.6	0.5
F4	black	98.3	2.9	27.3	30.1	-1.4	-0.8	2.0	1.8
A5	paper white	100.0	0.4	95.7	95.9	-0.2	-0.4	1.2	1.5
B5	Skin highlight L*=88	67.6	6.4	85.4	86.9	10.5	9.5	14.2	8.1
C5	Skin highlight L* =75	74.2	7.4	73.7	76.1	16.9	16.0	18.6	11.7
D5	Skin shadow L*=28	95.9	3.0	29.6	32.4	12.2	12.8	12.7	11.6
E5	Skin shadow L*=13	98.5	2.7	21.3	23.9	10.4	10.6	10.1	9.4
F5	Maximum Black	96.7	3.2	15.1	18.2	-3.0	-2.4	1.0	1.5
Summary Results		I* Color	I* tone	ΔE	100 Megalux hours				
Average Score for all patches		88.0	92.5	4.9					
Worst 10% (3 lowest scoring patches)		71.5	89.2	9.6					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	83.0	4.8	41.2	44.7	11.0	12.3	12.4	9.3
B1	Light Skin	68.7	8.1	65.9	69.1	14.9	15.4	16.7	9.2
C1	Blue sky	88.1	4.4	51.9	55.3	-5.9	-3.9	-17.6	-19.4
D1	Foliage	70.2	7.9	45.7	48.7	-11.9	-10.4	19.7	12.5
E1	blue flower	95.3	4.0	56.2	59.9	6.3	7.1	-21.0	-19.7
F1	bluish green	65.0	12.1	70.0	72.6	-32.3	-28.4	2.2	-8.9
A1	orange	86.1	8.9	62.5	64.9	31.8	30.6	48.6	40.2
B2	purplish blue	90.9	5.3	42.8	46.2	7.0	6.1	-38.8	-34.9
C2	moderate red	94.3	3.8	51.8	54.1	42.4	42.7	12.8	9.8
D2	purple	95.5	3.3	35.1	37.9	18.7	20.3	-17.9	-17.2
E2	yellow green	77.8	13.4	72.2	75.1	-23.0	-23.2	51.6	38.6
F2	orange yellow	82.4	11.7	71.0	73.7	16.0	13.7	59.9	48.7
A3	blue	93.5	4.2	33.9	36.6	9.5	8.3	-41.3	-38.3
B3	green	78.0	11.0	56.7	59.9	-34.7	-34.0	29.6	19.1
C3	red	94.2	4.1	43.6	45.6	47.7	48.5	22.8	19.3
D3	yellow	84.4	12.1	79.9	82.3	1.9	-1.0	72.7	61.2
E3	magenta	86.1	7.7	52.3	55.2	45.6	44.2	-13.2	-6.2
F3	cyan	87.1	5.8	53.7	57.3	-22.2	-19.2	-21.5	-24.8
A4	white	96.8	0.9	92.8	93.1	-0.7	-0.8	2.7	1.9
B4	neutral 8	76.5	3.2	79.0	80.8	-1.8	-1.8	2.5	-0.3
C4	neutral 6.5	72.0	4.5	66.9	70.1	-2.1	-1.3	1.7	-1.4
D4	neutral 5	74.0	4.8	53.0	56.8	-1.5	-0.3	2.7	0.0
E4	neutral 3.5	85.3	4.0	40.5	44.0	-1.2	0.1	1.6	0.2
F4	black	96.1	3.2	27.3	30.4	-1.4	-0.6	2.0	1.7
A5	paper white	92.3	1.2	95.7	95.7	-0.2	-0.5	1.2	2.4
B5	Skin highlight L*=88	65.7	6.7	85.4	87.0	10.5	9.3	14.2	7.7
C5	Skin highlight L* =75	68.3	9.0	73.7	76.6	16.9	16.2	18.6	10.2
D5	Skin shadow L*=28	92.4	3.6	29.6	32.7	12.2	13.2	12.7	11.1
E5	Skin shadow L*=13	96.2	3.2	21.3	24.3	10.4	10.6	10.1	9.1
F5	Maximum Black	97.0	3.8	15.1	18.7	-3.0	-2.4	1.0	1.4
Summary Results		I* Color	I* tone	ΔE	120 Megalux hours				
Average Score for all patches		84.4	91.3	6.0					
Worst 10% (3 lowest scoring patches)		66.3	87.2	12.5					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat




Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	77.8	5.6	41.2	44.9	11.0	12.6	12.4	8.5
B1	Light Skin	58.5	10.4	65.9	69.4	14.9	15.7	16.7	7.0
C1	Blue sky	80.0	5.7	51.9	55.7	-5.9	-3.4	-17.6	-20.9
D1	Foliage	64.6	9.3	45.7	49.2	-11.9	-10.1	19.7	11.2
E1	blue flower	96.1	4.5	56.2	60.4	6.3	7.6	-21.0	-20.8
F1	bluish green	56.8	14.7	70.0	72.9	-32.3	-27.4	2.2	-11.4
A1	orange	82.9	10.7	62.5	65.2	31.8	30.6	48.6	38.3
B2	purplish blue	92.9	5.0	42.8	46.7	7.0	6.8	-38.8	-35.6
C2	moderate red	91.6	4.9	51.8	54.3	42.4	43.5	12.8	8.7
D2	purple	95.1	3.6	35.1	38.2	18.7	20.5	-17.9	-18.2
E2	yellow green	72.9	16.2	72.2	75.5	-23.0	-23.1	51.6	35.8
F2	orange yellow	78.8	14.0	71.0	74.1	16.0	13.6	59.9	46.5
A3	blue	95.6	3.7	33.9	36.8	9.5	8.7	-41.3	-39.1
B3	green	73.2	13.2	56.7	60.3	-34.7	-33.9	29.6	16.9
C3	red	92.2	5.1	43.6	45.9	47.7	48.9	22.8	18.3
D3	yellow	80.6	14.9	79.9	82.7	1.9	-1.5	72.7	58.5
E3	magenta	87.4	7.3	52.3	55.6	45.6	44.7	-13.2	-6.8
F3	cyan	81.6	7.3	53.7	57.6	-22.2	-18.6	-21.5	-26.5
A4	white	82.5	2.2	92.8	93.2	-0.7	-0.6	2.7	0.5
B4	neutral 8	58.5	4.8	79.0	81.0	-1.8	-1.5	2.5	-2.0
C4	neutral 6.5	56.2	5.9	66.9	70.5	-2.1	-1.0	1.7	-2.8
D4	neutral 5	61.9	5.8	53.0	57.1	-1.5	0.0	2.7	-1.2
E4	neutral 3.5	77.3	4.7	40.5	44.4	-1.2	0.4	1.6	-0.6
F4	black	92.0	3.6	27.3	30.6	-1.4	-0.4	2.0	1.2
A5	paper white	100.0	0.2	95.7	95.9	-0.2	-0.4	1.2	1.3
B5	Skin highlight L*=88	50.1	9.5	85.4	87.2	10.5	9.8	14.2	4.9
C5	Skin highlight L* =75	58.3	11.5	73.7	77.0	16.9	16.5	18.6	7.6
D5	Skin shadow L*=28	89.1	4.2	29.6	33.0	12.2	13.4	12.7	10.6
E5	Skin shadow L*=13	94.2	3.6	21.3	24.7	10.4	10.7	10.1	8.8
F5	Maximum Black	93.6	4.4	15.1	19.3	-3.0	-2.1	1.0	1.6
Summary Results		I* Color	I* tone	ΔE	140 Megalux hours				
Average Score for all patches		79.1	90.6	7.2					
Worst 10% (3 lowest scoring patches)		54.4	86.0	15.3					

Epson Stylus Pro 9800, Epson OEM (K3 Ultrachrome), IJ Technologies Black Diamond Gloss Canvas, IJ Technologies Black Diamond Eclipse Top Coat



Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin	73.3	6.2	41.2	45.1	11.0	12.8	12.4	7.8
B1	Light Skin	52.7	11.7	65.9	69.7	14.9	16.0	16.7	5.7
C1	Blue sky	76.1	6.4	51.9	56.0	-5.9	-2.8	-17.6	-21.4
D1	Foliage	57.9	10.8	45.7	49.3	-11.9	-9.7	19.7	9.7
E1	blue flower	94.4	4.7	56.2	60.6	6.3	8.0	-21.0	-21.1
F1	bluish green	50.8	16.7	70.0	73.0	-32.3	-26.6	2.2	-13.2
A1	orange	79.6	12.7	62.5	65.4	31.8	30.8	48.6	36.3
B2	purplish blue	92.9	5.2	42.8	46.9	7.0	6.9	-38.8	-35.6
C2	moderate red	89.9	5.7	51.8	54.5	42.4	43.8	12.8	8.0
D2	purple	93.7	4.1	35.1	38.6	18.7	20.8	-17.9	-18.3
E2	yellow green	67.6	19.1	72.2	75.8	-23.0	-22.7	51.6	32.8
F2	orange yellow	75.1	16.2	71.0	74.2	16.0	13.7	59.9	44.1
A3	blue	95.7	3.9	33.9	37.0	9.5	8.9	-41.3	-39.0
B3	green	67.7	15.7	56.7	60.5	-34.7	-33.1	29.6	14.4
C3	red	90.4	6.1	43.6	46.1	47.7	49.1	22.8	17.4
D3	yellow	76.9	17.5	79.9	82.8	1.9	-1.5	72.7	55.8
E3	magenta	86.7	7.6	52.3	55.7	45.6	44.8	-13.2	-6.4
F3	cyan	78.3	8.3	53.7	57.9	-22.2	-18.1	-21.5	-27.3
A4	white	83.4	2.1	92.8	93.1	-0.7	-0.6	2.7	0.6
B4	neutral 8	54.6	5.2	79.0	81.1	-1.8	-1.3	2.5	-2.3
C4	neutral 6.5	48.5	6.5	66.9	70.6	-2.1	-0.7	1.7	-3.5
D4	neutral 5	54.5	6.5	53.0	57.4	-1.5	0.4	2.7	-1.8
E4	neutral 3.5	71.7	5.2	40.5	44.6	-1.2	0.6	1.6	-1.1
F4	black	89.2	3.8	27.3	30.8	-1.4	-0.2	2.0	1.0
A5	paper white	100.0	0.2	95.7	95.8	-0.2	-0.3	1.2	1.5
B5	Skin highlight L*=88	46.0	10.2	85.4	87.3	10.5	10.0	14.2	4.2
C5	Skin highlight L* =75	52.7	12.8	73.7	77.0	16.9	16.8	18.6	6.2
D5	Skin shadow L*=28	85.0	4.8	29.6	33.3	12.2	13.7	12.7	9.9
E5	Skin shadow L*=13	91.8	4.1	21.3	25.0	10.4	10.8	10.1	8.5
F5	Maximum Black	93.9	4.4	15.1	19.3	-3.0	-2.0	1.0	1.4
Summary Results		I* Color	I* tone	ΔE	160 Megalux hours				
Average Score for all patches		75.7	89.9	8.2					
Worst 10% (3 lowest scoring patches)		48.5	85.3	17.8					

The 180 Megalux hour Update will be posted on approximately OCT 05, 2014.



Original Print Colors before light exposure



Colors After light exposure

Patch #	Description	I* Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Dark Skin			41.2		11.0		12.4	
B1	Light Skin			65.9		14.9		16.7	
C1	Blue sky			51.9		-5.9		-17.6	
D1	Foliage			45.7		-11.9		19.7	
E1	blue flower			56.2		6.3		-21.0	
F1	bluish green			70.0		-32.3		2.2	
A1	orange			62.5		31.8		48.6	
B2	purplish blue			42.8		7.0		-38.8	
C2	moderate red			51.8		42.4		12.8	
D2	purple			35.1		18.7		-17.9	
E2	yellow green			72.2		-23.0		51.6	
F2	orange yellow			71.0		16.0		59.9	
A3	blue			33.9		9.5		-41.3	
B3	green			56.7		-34.7		29.6	
C3	red			43.6		47.7		22.8	
D3	yellow			79.9		1.9		72.7	
E3	magenta			52.3		45.6		-13.2	
F3	cyan			53.7		-22.2		-21.5	
A4	white			92.8		-0.7		2.7	
B4	neutral 8			79.0		-1.8		2.5	
C4	neutral 6.5			66.9		-2.1		1.7	
D4	neutral 5			53.0		-1.5		2.7	
E4	neutral 3.5			40.5		-1.2		1.6	
F4	black			27.3		-1.4		2.0	
A5	paper white			95.7		-0.2		1.2	
B5	Skin highlight L*=88			85.4		10.5		14.2	
C5	Skin highlight L* =75			73.7		16.9		18.6	
D5	Skin shadow L*=28			29.6		12.2		12.7	
E5	Skin shadow L*=13			21.3		10.4		10.1	
F5	Maximum Black			15.1		-3.0		1.0	
Summary Results		I* Color	I* tone	ΔE	180 Megalux hours				
Average Score for all patches									
Worst 10% (3 lowest scoring patches)									