




Accelerated Light Fading Test Results

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*

Sample # AaI_20100202_SN003

140 Megalux-hours completed

Conservation Display Rating *	
Lower Exposure Limit (Megalux hours)	Upper Exposure limit (Megalux hours)
6	6


* Please read document **AaI_2009_0118_TA-01.pdf**, "An Overview of the AaI&A Conservation Display Ratings", located on the Documents page of the AaI&A website for an explanation of the conservation display ratings.

Document #: AaI_20100202_SN003Lf.pdf Rev: June 13, 2013

Test Print Prepared by: AaI&A Member

Copyright 2013. This report has been prepared for the exclusive use of members of Aardenburg Imaging & Archives. Members may share this information with other members, friends, colleagues, and individual clients. It may also be distributed to groups for educational purposes (classes, lectures, educational seminars. etc). However, all contents including but not limited to Conservation Display Ratings may not be posted to web sites and may not be reproduced or distributed for corporate research, marketing, or other promotional purposes without written permission from Aardenburg Imaging & Archives.


For more information please contact: info@aardenburg-imaging.com



About this Report

This report contains light fastness information about a single test print produced by a specific digital printing system. “System” refers to all hardware, software, and materials used to make the finished print. The hardware, software, material components, and printmaker’s skills contribute to the final image quality and image permanence. The tested sample is made with current or recently discontinued stocks of commercially available products unless otherwise stated. Each sample has been prepared by Aardenburg Imaging & Archives or one of its members in accordance with customary print making practices unless otherwise noted. The sample may also contain additional finishing materials such as overcoats and laminates which are also noted when used. Finally, the sample has been tested under standardized conditions that are defined on the Sample Description page (see page 2). AaI&A makes every effort to ensure but cannot guarantee that the samples are properly identified and documented and that test results are accurate. For this reason, AaI&A also strives to test independently produced sample replicates in order to increase sampling confidence and to provide information on process variability. Please compare the results in this report to replicate test samples when the data become available.

Understanding the Test Results



AaI_StandardB&Wset(v2).tif


The magnitude and visual appearance of fading depends not only on the chosen printing system but the chosen image as well. In other words, different images are comprised of different colors, and the fading relationships between those colors dictate how the image will look as it fades. The sample print in this test report was made by printing the digital image shown on the left. This image is designed specifically for monochrome printing applications. It contains 30 neutral colors ranging from maximum white ($L^* = 100$, $a^* = 0$, $b^* = 0$) to maximum black ($L^* = 0$, $a^* = 0$, $b^* = 0$). Any hue and chroma observed in the “Original Print Colors” were achieved by the printmaker’s selection of media, RIP/driver settings, and choice of inks installed in the printer. The actual sample appearance reproduced in this report is digitally mastered from the colorimetric measurements of the test sample.

Information about the fading characteristics of the product is provided in three ways:``

1) ***You can visually assess the fading.*** The target images reproduced in this report are digitally reconstructed from the spectrally measured color data rather than scanning or otherwise reproducing the physical print by conventional techniques. This method ensures a colorimetrically accurate representation of the print appearance as the print fades. A calibrated monitor is recommended to experience the best possible reproduction of the test sample appearance. The side-by-side presentation of the target images simulates looking at the light-exposed print along side a perfect duplicate of the unexposed original print. The “Before/After” Layer mode takes advantage of Adobe Reader Layer technology. Toggle the “Before/After” layer on and off using the layers feature of Adobe Reader to directly switch between the light exposed print colors and the initial print colors for the image located on the right side of each page. Also, use Adobe Reader’s full screen mode to cycle through the pages and “animate” the fading.

2) ***I* Color and tonal accuracy scores are reported.*** This report includes I* metric scores that compare the color and tonal relationships of the light exposed samples to the color and tonal relationships existing in the original print prior to light exposure. Perfect I* scores of 100% can be approached when no significant fading occurs. Average scores above 90% generally indicate excellent retention of original quality, 80% good, 70% fair, etc., but your conclusions may vary depending on your image quality requirements. ***I* color*** rates the retained color accuracy (hue and chroma) while ***I* tone*** rates the retained tonal accuracy (lightness and contrast). The score is on a percentile scale where 100% is a perfect match between the comparison image (e.g., “after” light exposure) and the reference image (e.g., “before” any light exposure). 0% ***I* color*** means no color accuracy is left. 0% ***I* tone*** means essentially no tonality remains and all image information content is lost. Negative I* values have significance as well and contribute to the average I* score when they occur. Negative I* color values mean false color has occurred, for example, when a skin tone turns green or a neutral gray becomes distinctly colorful. Negative I* tone scores mean visual contrast between colors has become inverted (i.e., like the tonal relationships in a photographic film negative). Serious image quality problems must arise before false colors and/or tones appear. For more information on the I* metric, please refer to the AaI&A web site.


3) ***Color changes are also reported using the classic color difference model, ΔE .*** Note that ΔE values lose perceptual scaling significance when they become large (e.g., > 15). Also, the ΔE equation does not unambiguously measure changes in image contrast. This limitation is generally not a problem for paints and textiles, but can be a serious oversight when evaluating photographic images. It was a major reason behind the development of the I* metric.



Sample Description

Printer: Epson Stylus Pro 7000
Ink: Cone Piezography Carbon Sepia K6
Paper: PremierArt™ Alise Bright White

Sample #: AaI_20100202_SN003
Test Print Prepared by: AaI&A member



AaI_StandardB&Wset(v2).tif

Test Image: AaI_StandardB&Wset(v2).tif
RIP/Driver settings: PSCS3, no adjustment
Media Setting: QTR Matte Photo
Printed: February 2, 2010
Original print colors measured on: February 21, 2010
Test started on: February 22, 2010

Profile: n.a. **Rendering Intent:** n.a.
Profile type: n.a.
Profile Creation Software: n.a.

Paper White Color (UV–included versus UV–excluded) and Maximum Printed Black						
Optical Brighteners present? yes	L*		a*		b*	
	UV inc	UV exc	UV inc	UV exc	UV inc	UV exc
Maximum Paper White (no colorants printed)	97.5	97.5	0.7	0.0	-3.6	1.8
(1) ΔL*, Δa*, Δb* respectively	0.0		0.7		5.4	
(1) Calculated differences, especially for Δb*, indicate the role and magnitude of fluorescence on original paper color						
Maximum Printed black (UV included)	L* = 15.8		a* = 0.4		b* = 0.6	

Light Source: Phillips Colortone F40T12/C50
Filter/Glazing: Sample framed under Glass*
Light Exposure Cycle: 8 hours on, 4 hours off, twice per 24 hours
Average Illuminance during “on” cycle: 10,716 Lux
Average Temperature: 23.7°C over full test duration, 25.4°C during light exposure
Average Relative humidity: 59.4%RH full test period, 59.8%RH during light exposure
CIELAB measurements: D50 2° observer, Xrite Gretag/Macbeth Spectrolino/Spectroscan

Replicates/Compare to:

No Replicates are available at this time.

Notes/Comments:

* The Phillips Colortone F40T12/C50 fluorescent light source and ordinary glass picture frame glazing yields UVA content and overall spectral power similar to natural 5000°K daylight entering a window and then striking a print that has been framed by **standard acrylic glazing** rather than ordinary glass. Other light sources and/or different glazing options may yield greater or lesser fade rates (generally, a 2-5x increase in fade rate for direct sunlight compared to UV-excluded sources at the same Lux level). The spectral quality of the light can also affect individual colors differently.

April 26, 2010 – 10 Megalux hours: Much if not all of the low Conservation Display rating score for this printer/ink/media combination can be attributed to the early loss of optical brightener activity in the paper. The resultant media white point shift affects the hue of the print sample throughout the highlights and well into the midtones because the light and midtone shades of the ink do not have enough covering power to conceal the change in media color underneath. It is this visual “transparency” of the Piezography ink shades that gives the Piezography K6 ink set its distinctive visual character, but this aesthetic quality leaves the system more vulnerable to the color constancy of the media over time. The large percentage of affected highlights and midtones in the AaI_StandardB&Wset(v2).tif target account for both limits of the Conservation display rating (CDR) being reached at the same exposure dose.

Table to Convert Megalux-hours of Light Exposure to estimated “Years on Display”												
Indoor Light Levels for Print Display		Multiply Mlux-hrs by	Megalux-hours in test									
Light Exposure	Description		10	20	30	40	50	60	70	80	90	100
≤ 10 Lux 24 hours per day	Interior rooms, storage areas, or hallways without windows, illuminated sparingly by artificial lighting	11.42	114	228	342	457	571	685	799	913	1027	1142
50 Lux 12 hours per day	“Museum Standard” display condition	4.57	46	91	137	183	228	274	325	365	411	457
120 Lux 12 hours per day “Kodak Display Years” (1)	Average home illumination level for photos is ~ 60 lux. 90% of all displayed photos do not exceed 120 lux (1).	1.90	19	38	57	76	95	114	133	152	171	190
228 Lux 12 hours per day	Relatively bright home or office. Note the simple 1:1 relationship between “years on display” and Mlux-hr values at this condition.	1.00	10	20	30	40	50	60	70	80	90	100
450 Lux 12 hours per day “WIR Display Years” (2) Also equals 500 lux for 11.8 hours per day	A bright home or commercial office building illumination level is 200-500 lux. Also, good illumination for color critical viewing and color matching tasks begins at about 500 lux.	0.51	5	10	15	20	25	30	35	41	46	51
2000 Lux 12 hours per day	Commercial Gallery. Also, critical color evaluation standards call for 2000 lux and a D50 illumination source.	0.114	1.1	2.3	3.4	4.6	5.7	6.8	8.0	9.1	10.3	11.4
5000 Lux 12 hours per day	E.g., Sunlight through a window striking print at an angle.	0.046	0.5	0.9	1.4	1.8	2.3	2.7	3.2	3.7	4.1	4.6
10,000 Lux 12 hours per day	South-facing window in U.S.A. , e.g., storefront display with photos directly facing window.	0.023	0.2	0.5	0.7	0.9	1.1	1.4	1.6	1.8	2.1	2.3


Light levels commonly encountered in the real world fluctuate widely throughout indoor print display environments and produce large variations in how long it takes for artwork to acquire light-induced damage. Use this table as a guide to estimate how many “years on display” (denoted in red text) it takes to accumulate the light exposure test dosage. Review the test results to decide which Megalux-hour dose has caused fading to your level of concern (e.g., just noticeable, easily noticeable, objectionable, etc.). Then choose the print display description that best represents how your print is likely to be displayed. You may want to obtain a lux meter and make some measurements in your own display environment!

Note that as the years of display time increase, light-induced fading can be eclipsed by other serious aging mechanisms such as fading and/or staining caused by heat, humidity, and air pollutants. Mould damage can also occur at high humidity. Even when colorants remain water fast, direct contact with liquids may result in physical deformation and staining of the substrate. Also, temperature and especially humidity cycling can cause physical cracks and/or flaking, etc. Handling damage such as scratching, abrasion, tears and creases, and catastrophic damage by smoke, fire, flood, etc., also degrade print quality over time. Thus, as illumination levels are reduced other forms of degradation take on greater proportion of risk and may appear in shorter time intervals.


(1) Eastman Kodak has cited this exposure condition and 90% confidence limit as a rationale for estimating print fading times of traditional color photo materials in typical home display environments. For recent light fading claims regarding its line of pigment-based inkjet printers, Kodak has adopted the higher level of 450lux/12 hours per day which is also used by Wilhelm Imaging Research, Inc. (See below).

(2) Wilhelm Imaging Research (WIR) has standardized its light fastness ratings on 450 lux for 12 hours per day in order to estimate the years on display necessary to reach “noticeable” fading. This average light exposure condition, an assumed 75°F/60%RH temperature and humidity level, and WIR’s visually weighted densitometric endpoint criteria set V3.0 has become a de facto industry standard for most predictive light fading estimates in the absence of a published International Standards Organization (ISO) test standard.

100_{color}/100_{tone}




Original Print Colors
(measured before light exposure)




Colors at **Zero Megalux-hours** of Light Exposure
(same as original print colors)

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


Original Print Colors as Measured and at Start of Test

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	100.0	0.0	97.6		1.6		-3.3	
B1	Highlight L* = 96	100.0	0.0	94.2		2.0		-2.0	
C1	Highlight L* = 89	100.0	0.0	88.0		2.5		0.0	
D1	Highlight L* = 78	100.0	0.0	79.5		2.8		2.1	
E1	Midtone L* = 66	100.0	0.0	71.0		2.9		2.2	
F1	Midtone L* = 52	100.0	0.0	61.8		2.9		2.7	
A2	Highlight L* = 92	100.0	0.0	90.5		2.3		-0.9	
B2	Highlight L* = 85	100.0	0.0	84.8		2.6		0.9	
C2	Highlight L* = 75	100.0	0.0	77.1		2.9		2.1	
D2	Midtone L* = 63	100.0	0.0	69.5		2.8		2.2	
E2	Midtone L* = 50	100.0	0.0	60.8		2.8		2.8	
F2	Midtone L* = 38	100.0	0.0	52.1		2.6		2.8	
A3	Highlight L* = 82	100.0	0.0	82.5		2.7		1.3	
B3	Midtone L* = 72	100.0	0.0	74.8		2.9		2.2	
C3	Midtone L* = 60	100.0	0.0	67.6		2.9		2.3	
D3	Midtone L* = 47	100.0	0.0	59.0		2.8		2.9	
E3	Midtone L* = 35	100.0	0.0	50.5		2.5		2.6	
F3	Shadow L* = 25	100.0	0.0	41.5		2.2		2.2	
A4	Midtone L* = 69	100.0	0.0	72.8		2.9		2.0	
B4	Midtone L* = 57	100.0	0.0	65.5		2.9		2.5	
C4	Midtone L* = 45	100.0	0.0	57.3		2.7		2.8	
D4	Midtone L* = 32	100.0	0.0	48.2		2.4		2.5	
E4	Shadow L* = 20	100.0	0.0	37.1		2.0		2.0	
F4	Shadow L* = 10	100.0	0.0	23.5		1.1		0.6	
A5	Midtone L* = 55	100.0	0.0	64.0		2.9		2.5	
B5	Midtone L* = 41	100.0	0.0	54.6		2.7		2.8	
C5	Shadow L* = 29	100.0	0.0	44.9		2.4		2.5	
D5	Shadow L* = 15	100.0	0.0	30.3		1.6		1.5	
E5	Shadow L* = 5	100.0	0.0	20.6		0.8		0.4	
F5	Max Black	100.0	0.0	15.8		0.4		0.6	
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		100	100	0.0					
Average Score for the Worst 10% (3 lowest scoring patches)		100	100	0.0					

84.6_{color} / 98.2_{tone}



Original Print Colors
(measured before light exposure)




Colors after 10 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


10 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	73.5	3.0	97.6	97.7	1.6	0.6	-3.3	-0.4
B1	Highlight L* = 96	73.9	3.0	94.2	94.3	2.0	1.0	-2.0	0.8
C1	Highlight L* = 89	74.6	2.9	88.0	88.2	2.5	1.5	0.0	2.7
D1	Highlight L* = 78	77.6	2.6	79.5	79.6	2.8	2.0	2.1	4.6
E1	Midtone L* = 66	79.3	2.5	71.0	70.9	2.9	2.2	2.2	4.5
F1	Midtone L* = 52	84.1	2.0	61.8	61.6	2.9	2.4	2.7	4.7
A2	Highlight L* = 92	73.9	3.0	90.5	90.6	2.3	1.3	-0.9	1.9
B2	Highlight L* = 85	75.6	2.8	84.8	84.9	2.6	1.7	0.9	3.6
C2	Highlight L* = 75	77.3	2.7	77.1	77.1	2.9	2.2	2.1	4.6
D2	Midtone L* = 63	80.1	2.4	69.5	69.4	2.8	2.2	2.2	4.5
E2	Midtone L* = 50	84.8	2.0	60.8	60.5	2.8	2.4	2.8	4.7
F2	Midtone L* = 38	88.9	1.6	52.1	51.6	2.6	2.3	2.8	4.3
A3	Highlight L* = 82	75.9	2.8	82.5	82.6	2.7	1.9	1.3	3.9
B3	Midtone L* = 72	77.8	2.6	74.8	74.7	2.9	2.2	2.2	4.7
C3	Midtone L* = 60	81.0	2.3	67.6	67.4	2.9	2.3	2.3	4.5
D3	Midtone L* = 47	85.8	1.9	59.0	58.8	2.8	2.4	2.9	4.7
E3	Midtone L* = 35	89.4	1.6	50.5	50.1	2.5	2.2	2.6	4.1
F3	Shadow L* = 25	93.1	1.3	41.5	40.8	2.2	2.0	2.2	3.4
A4	Midtone L* = 69	78.2	2.6	72.8	72.7	2.9	2.2	2.0	4.5
B4	Midtone L* = 57	82.3	2.2	65.5	65.3	2.9	2.4	2.5	4.6
C4	Midtone L* = 45	86.4	1.8	57.3	57.0	2.7	2.4	2.8	4.5
D4	Midtone L* = 32	90.3	1.5	48.2	47.7	2.4	2.1	2.5	3.9
E4	Shadow L* = 20	94.9	1.2	37.1	36.4	2.0	1.8	2.0	2.9
F4	Shadow L* = 10	99.7	0.8	23.5	23.0	1.1	0.9	0.6	1.1
A5	Midtone L* = 55	82.6	2.2	64.0	63.7	2.9	2.4	2.5	4.6
B5	Midtone L* = 41	87.6	1.7	54.6	54.3	2.7	2.4	2.8	4.5
C5	Shadow L* = 29	91.8	1.4	44.9	44.3	2.4	2.1	2.5	3.8
D5	Shadow L* = 15	97.7	1.0	30.3	29.7	1.6	1.5	1.5	2.2
E5	Shadow L* = 5	100.0	0.5	20.6	20.3	0.8	0.7	0.4	0.8
F5	Max Black	100.0	0.3	15.8	15.9	0.4	0.5	0.6	0.9
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		84.6	98.2	2.0					
Average Score for the Worst 10% (3 lowest scoring patches)		73.8	96.6	3.0					

80.7_{color} / 98.1_{tone}



Original Print Colors
(measured before light exposure)



Colors after 20 Megalux-hours
light exposure


*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*

20 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	63.6	4.0	97.6	97.7	1.6	0.3	-3.3	0.5
B1	Highlight L* = 96	64.5	3.9	94.2	94.2	2.0	0.7	-2.0	1.6
C1	Highlight L* = 89	66.9	3.6	88.0	88.1	2.5	1.3	0.0	3.4
D1	Highlight L* = 78	72.9	3.1	79.5	79.6	2.8	1.9	2.1	5.0
E1	Midtone L* = 66	75.6	2.8	71.0	71.0	2.9	2.1	2.2	4.9
F1	Midtone L* = 52	80.8	2.3	61.8	61.6	2.9	2.3	2.7	5.0
A2	Highlight L* = 92	64.9	3.8	90.5	90.6	2.3	1.0	-0.9	2.7
B2	Highlight L* = 85	69.1	3.4	84.8	84.9	2.6	1.5	0.9	4.2
C2	Highlight L* = 75	72.4	3.1	77.1	77.1	2.9	2.0	2.1	5.1
D2	Midtone L* = 63	76.5	2.7	69.5	69.4	2.8	2.1	2.2	4.8
E2	Midtone L* = 50	81.9	2.2	60.8	60.6	2.8	2.3	2.8	4.9
F2	Midtone L* = 38	86.2	1.9	52.1	51.7	2.6	2.2	2.8	4.5
A3	Highlight L* = 82	69.8	3.4	82.5	82.6	2.7	1.7	1.3	4.5
B3	Midtone L* = 72	73.7	3.0	74.8	74.7	2.9	2.1	2.2	5.1
C3	Midtone L* = 60	77.4	2.7	67.6	67.4	2.9	2.2	2.3	4.9
D3	Midtone L* = 47	82.6	2.2	59.0	58.8	2.8	2.3	2.9	5.0
E3	Midtone L* = 35	86.7	1.8	50.5	50.1	2.5	2.2	2.6	4.4
F3	Shadow L* = 25	90.9	1.5	41.5	40.7	2.2	1.9	2.2	3.6
A4	Midtone L* = 69	73.8	3.0	72.8	72.7	2.9	2.1	2.0	4.9
B4	Midtone L* = 57	78.8	2.5	65.5	65.3	2.9	2.2	2.5	4.9
C4	Midtone L* = 45	83.4	2.1	57.3	57.0	2.7	2.3	2.8	4.8
D4	Midtone L* = 32	88.0	1.7	48.2	47.7	2.4	2.1	2.5	4.1
E4	Shadow L* = 20	93.1	1.3	37.1	36.4	2.0	1.7	2.0	3.1
F4	Shadow L* = 10	98.3	0.8	23.5	23.0	1.1	0.9	0.6	1.3
A5	Midtone L* = 55	79.0	2.5	64.0	63.7	2.9	2.3	2.5	5.0
B5	Midtone L* = 41	84.7	2.0	54.6	54.3	2.7	2.3	2.8	4.7
C5	Shadow L* = 29	89.3	1.6	44.9	44.4	2.4	2.1	2.5	4.0
D5	Shadow L* = 15	95.8	1.1	30.3	29.7	1.6	1.4	1.5	2.3
E5	Shadow L* = 5	99.6	0.6	20.6	20.4	0.8	0.7	0.4	0.9
F5	Max Black	100.0	0.4	15.8	15.9	0.4	0.5	0.6	1.0


Summary Results

I*Color	I*tone	ΔE
80.7	98.1	2.4
64.3	96.7	3.9




AARDENBURG IMAGING
& ARCHIVES

79.5_{color} / 98.1_{tone}



Original Print Colors
(measured before light exposure)




Colors after 30 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


30 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	61.2	4.2	97.6	97.7	1.6	0.2	-3.3	0.7
B1	Highlight L* = 96	61.8	4.1	94.2	94.3	2.0	0.6	-2.0	1.9
C1	Highlight L* = 89	65.0	3.8	88.0	88.2	2.5	1.2	0.0	3.6
D1	Highlight L* = 78	71.6	3.2	79.5	79.6	2.8	1.9	2.1	5.1
E1	Midtone L* = 66	74.5	2.9	71.0	71.0	2.9	2.1	2.2	5.0
F1	Midtone L* = 52	79.7	2.4	61.8	61.7	2.9	2.3	2.7	5.1
A2	Highlight L* = 92	62.5	4.1	90.5	90.7	2.3	1.0	-0.9	3.0
B2	Highlight L* = 85	67.4	3.6	84.8	85.0	2.6	1.5	0.9	4.3
C2	Highlight L* = 75	71.1	3.2	77.1	77.2	2.9	2.0	2.1	5.2
D2	Midtone L* = 63	75.5	2.8	69.5	69.5	2.8	2.1	2.2	4.9
E2	Midtone L* = 50	80.7	2.3	60.8	60.6	2.8	2.3	2.8	5.0
F2	Midtone L* = 38	85.3	1.9	52.1	51.8	2.6	2.2	2.8	4.6
A3	Highlight L* = 82	67.9	3.6	82.5	82.7	2.7	1.7	1.3	4.7
B3	Midtone L* = 72	72.5	3.1	74.8	74.8	2.9	2.0	2.2	5.2
C3	Midtone L* = 60	76.2	2.8	67.6	67.5	2.9	2.2	2.3	5.0
D3	Midtone L* = 47	81.7	2.2	59.0	58.9	2.8	2.3	2.9	5.0
E3	Midtone L* = 35	85.6	1.9	50.5	50.1	2.5	2.1	2.6	4.5
F3	Shadow L* = 25	90.0	1.5	41.5	40.9	2.2	1.9	2.2	3.7
A4	Midtone L* = 69	72.7	3.1	72.8	72.8	2.9	2.0	2.0	5.0
B4	Midtone L* = 57	77.5	2.6	65.5	65.4	2.9	2.2	2.5	5.1
C4	Midtone L* = 45	82.7	2.2	57.3	57.0	2.7	2.2	2.8	4.9
D4	Midtone L* = 32	87.4	1.8	48.2	47.7	2.4	2.0	2.5	4.1
E4	Shadow L* = 20	92.3	1.4	37.1	36.5	2.0	1.7	2.0	3.2
F4	Shadow L* = 10	97.9	0.8	23.5	23.2	1.1	0.9	0.6	1.3
A5	Midtone L* = 55	78.1	2.6	64.0	63.8	2.9	2.2	2.5	5.0
B5	Midtone L* = 41	84.0	2.0	54.6	54.3	2.7	2.2	2.8	4.8
C5	Shadow L* = 29	88.4	1.7	44.9	44.4	2.4	2.0	2.5	4.1
D5	Shadow L* = 15	94.9	1.1	30.3	29.8	1.6	1.4	1.5	2.4
E5	Shadow L* = 5	99.6	0.6	20.6	20.3	0.8	0.7	0.4	0.9
F5	Max Black	100.0	0.3	15.8	15.9	0.4	0.5	0.6	1.0
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		79.5	98.1	2.5					
Average Score for the Worst 10% (3 lowest scoring patches)		61.8	97.1	4.1					

77.9_{color} / 97.8_{tone}



Original Print Colors
(measured before light exposure)




Colors after 40 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


40 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	58.7	4.4	97.6	97.7	1.6	0.2	-3.3	0.9
B1	Highlight L* = 96	59.4	4.4	94.2	94.3	2.0	0.6	-2.0	2.1
C1	Highlight L* = 89	62.2	4.1	88.0	88.2	2.5	1.2	0.0	3.9
D1	Highlight L* = 78	69.6	3.4	79.5	79.7	2.8	1.9	2.1	5.3
E1	Midtone L* = 66	72.8	3.1	71.0	71.0	2.9	2.1	2.2	5.1
F1	Midtone L* = 52	78.2	2.6	61.8	61.6	2.9	2.3	2.7	5.2
A2	Highlight L* = 92	60.3	4.3	90.5	90.7	2.3	0.9	-0.9	3.2
B2	Highlight L* = 85	65.2	3.8	84.8	85.0	2.6	1.5	0.9	4.5
C2	Highlight L* = 75	69.1	3.4	77.1	77.1	2.9	2.0	2.1	5.4
D2	Midtone L* = 63	73.8	3.0	69.5	69.4	2.8	2.1	2.2	5.1
E2	Midtone L* = 50	79.1	2.5	60.8	60.6	2.8	2.3	2.8	5.2
F2	Midtone L* = 38	83.7	2.1	52.1	51.6	2.6	2.2	2.8	4.8
A3	Highlight L* = 82	65.9	3.7	82.5	82.7	2.7	1.6	1.3	4.8
B3	Midtone L* = 72	70.6	3.3	74.8	74.8	2.9	2.0	2.2	5.4
C3	Midtone L* = 60	74.7	2.9	67.6	67.4	2.9	2.2	2.3	5.1
D3	Midtone L* = 47	80.1	2.4	59.0	58.7	2.8	2.3	2.9	5.2
E3	Midtone L* = 35	84.6	2.0	50.5	50.0	2.5	2.2	2.6	4.6
F3	Shadow L* = 25	89.0	1.7	41.5	40.7	2.2	1.9	2.2	3.8
A4	Midtone L* = 69	71.1	3.2	72.8	72.7	2.9	2.1	2.0	5.2
B4	Midtone L* = 57	76.0	2.8	65.5	65.3	2.9	2.2	2.5	5.2
C4	Midtone L* = 45	80.7	2.3	57.3	57.0	2.7	2.3	2.8	5.1
D4	Midtone L* = 32	86.0	1.9	48.2	47.6	2.4	2.1	2.5	4.3
E4	Shadow L* = 20	91.1	1.6	37.1	36.3	2.0	1.7	2.0	3.3
F4	Shadow L* = 10	97.7	0.9	23.5	23.1	1.1	0.9	0.6	1.3
A5	Midtone L* = 55	76.3	2.8	64.0	63.7	2.9	2.2	2.5	5.2
B5	Midtone L* = 41	82.5	2.2	54.6	54.2	2.7	2.3	2.8	5.0
C5	Shadow L* = 29	87.4	1.8	44.9	44.2	2.4	2.1	2.5	4.2
D5	Shadow L* = 15	94.0	1.3	30.3	29.6	1.6	1.4	1.5	2.5
E5	Shadow L* = 5	98.8	0.7	20.6	20.3	0.8	0.7	0.4	1.0
F5	Max Black	100.0	0.4	15.8	15.9	0.4	0.5	0.6	1.0
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		77.9	97.8	2.6					
Average Score for the Worst 10% (3 lowest scoring patches)		59.4	97.0	4.4					

78.5_{color} / 98.0_{tone}




Original Print Colors
(measured before light exposure)




Colors after 50 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


50 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	59.8	4.3	97.6	97.8	1.6	0.1	-3.3	0.8
B1	Highlight L* = 96	60.6	4.2	94.2	94.3	2.0	0.5	-2.0	2.0
C1	Highlight L* = 89	63.2	4.0	88.0	88.2	2.5	1.2	0.0	3.8
D1	Highlight L* = 78	70.6	3.3	79.5	79.7	2.8	1.8	2.1	5.2
E1	Midtone L* = 66	73.5	3.0	71.0	71.0	2.9	2.1	2.2	5.1
F1	Midtone L* = 52	78.7	2.5	61.8	61.7	2.9	2.3	2.7	5.2
A2	Highlight L* = 92	60.9	4.2	90.5	90.7	2.3	0.9	-0.9	3.1
B2	Highlight L* = 85	66.0	3.7	84.8	85.1	2.6	1.4	0.9	4.5
C2	Highlight L* = 75	70.0	3.4	77.1	77.2	2.9	2.0	2.1	5.3
D2	Midtone L* = 63	74.3	2.9	69.5	69.4	2.8	2.1	2.2	5.0
E2	Midtone L* = 50	79.7	2.4	60.8	60.7	2.8	2.2	2.8	5.1
F2	Midtone L* = 38	84.2	2.0	52.1	51.7	2.6	2.2	2.8	4.7
A3	Highlight L* = 82	66.5	3.7	82.5	82.7	2.7	1.6	1.3	4.8
B3	Midtone L* = 72	71.3	3.2	74.8	74.8	2.9	2.0	2.2	5.3
C3	Midtone L* = 60	75.1	2.9	67.6	67.5	2.9	2.1	2.3	5.1
D3	Midtone L* = 47	80.7	2.3	59.0	58.8	2.8	2.3	2.9	5.1
E3	Midtone L* = 35	84.8	2.0	50.5	50.1	2.5	2.2	2.6	4.5
F3	Shadow L* = 25	89.1	1.7	41.5	40.8	2.2	1.9	2.2	3.7
A4	Midtone L* = 69	71.4	3.2	72.8	72.8	2.9	2.0	2.0	5.1
B4	Midtone L* = 57	76.4	2.7	65.5	65.4	2.9	2.2	2.5	5.2
C4	Midtone L* = 45	81.5	2.3	57.3	57.1	2.7	2.3	2.8	5.0
D4	Midtone L* = 32	86.2	1.9	48.2	47.7	2.4	2.1	2.5	4.3
E4	Shadow L* = 20	91.6	1.5	37.1	36.4	2.0	1.7	2.0	3.2
F4	Shadow L* = 10	97.6	0.9	23.5	23.1	1.1	0.9	0.6	1.3
A5	Midtone L* = 55	76.8	2.7	64.0	63.8	2.9	2.2	2.5	5.2
B5	Midtone L* = 41	82.9	2.1	54.6	54.3	2.7	2.2	2.8	4.9
C5	Shadow L* = 29	87.7	1.7	44.9	44.4	2.4	2.0	2.5	4.2
D5	Shadow L* = 15	94.3	1.2	30.3	29.7	1.6	1.4	1.5	2.5
E5	Shadow L* = 5	99.2	0.7	20.6	20.3	0.8	0.7	0.4	0.9
F5	Max Black	100.0	0.3	15.8	15.9	0.4	0.5	0.6	0.9
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		78.5	98.0	2.6					
Average Score for the Worst 10% (3 lowest scoring patches)		60.4	97.2	4.3					

78.4_{color} / 98.2_{tone}



Original Print Colors
(measured before light exposure)




Colors after 60 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


60 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	59.8	4.3	97.6	97.8	1.6	0.1	-3.3	0.8
B1	Highlight L* = 96	60.3	4.3	94.2	94.3	2.0	0.5	-2.0	2.0
C1	Highlight L* = 89	63.1	4.0	88.0	88.3	2.5	1.2	0.0	3.8
D1	Highlight L* = 78	70.6	3.3	79.5	79.7	2.8	1.8	2.1	5.2
E1	Midtone L* = 66	73.6	3.0	71.0	71.1	2.9	2.0	2.2	5.1
F1	Midtone L* = 52	78.7	2.5	61.8	61.8	2.9	2.2	2.7	5.2
A2	Highlight L* = 92	60.8	4.2	90.5	90.7	2.3	0.9	-0.9	3.1
B2	Highlight L* = 85	66.0	3.7	84.8	85.1	2.6	1.4	0.9	4.4
C2	Highlight L* = 75	69.9	3.4	77.1	77.2	2.9	1.9	2.1	5.3
D2	Midtone L* = 63	74.6	2.9	69.5	69.5	2.8	2.1	2.2	5.0
E2	Midtone L* = 50	79.6	2.4	60.8	60.7	2.8	2.2	2.8	5.1
F2	Midtone L* = 38	84.2	2.0	52.1	51.8	2.6	2.2	2.8	4.7
A3	Highlight L* = 82	66.4	3.7	82.5	82.7	2.7	1.6	1.3	4.8
B3	Midtone L* = 72	71.6	3.2	74.8	74.8	2.9	2.0	2.2	5.2
C3	Midtone L* = 60	75.3	2.9	67.6	67.5	2.9	2.1	2.3	5.1
D3	Midtone L* = 47	80.8	2.3	59.0	58.9	2.8	2.3	2.9	5.1
E3	Midtone L* = 35	84.6	2.0	50.5	50.2	2.5	2.1	2.6	4.6
F3	Shadow L* = 25	89.1	1.6	41.5	41.0	2.2	1.8	2.2	3.7
A4	Midtone L* = 69	71.6	3.2	72.8	72.9	2.9	2.0	2.0	5.1
B4	Midtone L* = 57	76.3	2.7	65.5	65.4	2.9	2.2	2.5	5.2
C4	Midtone L* = 45	81.7	2.2	57.3	57.1	2.7	2.2	2.8	5.0
D4	Midtone L* = 32	86.2	1.9	48.2	47.8	2.4	2.0	2.5	4.3
E4	Shadow L* = 20	91.4	1.4	37.1	36.6	2.0	1.7	2.0	3.3
F4	Shadow L* = 10	97.2	0.9	23.5	23.1	1.1	0.9	0.6	1.4
A5	Midtone L* = 55	76.7	2.7	64.0	63.8	2.9	2.2	2.5	5.2
B5	Midtone L* = 41	82.9	2.1	54.6	54.4	2.7	2.2	2.8	4.9
C5	Shadow L* = 29	87.4	1.7	44.9	44.5	2.4	2.0	2.5	4.2
D5	Shadow L* = 15	93.8	1.2	30.3	29.8	1.6	1.4	1.5	2.5
E5	Shadow L* = 5	98.5	0.7	20.6	20.3	0.8	0.7	0.4	1.0
F5	Max Black	100.0	0.4	15.8	15.8	0.4	0.4	0.6	1.0
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		78.4	98.2	2.6					
Average Score for the Worst 10% (3 lowest scoring patches)		60.3	97.5	4.3					

78.8_{color} / 98.3_{tone}



Original Print Colors
(measured before light exposure)




Colors after 70 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


70 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	59.7	4.3	97.6	97.7	1.6	0.1	-3.3	0.8
B1	Highlight L* = 96	60.0	4.3	94.2	94.2	2.0	0.5	-2.0	2.0
C1	Highlight L* = 89	62.9	4.0	88.0	88.3	2.5	1.1	0.0	3.8
D1	Highlight L* = 78	70.8	3.3	79.5	79.7	2.8	1.8	2.1	5.2
E1	Midtone L* = 66	74.0	3.0	71.0	71.1	2.9	2.0	2.2	5.0
F1	Midtone L* = 52	79.3	2.5	61.8	61.8	2.9	2.2	2.7	5.1
A2	Highlight L* = 92	60.5	4.2	90.5	90.7	2.3	0.9	-0.9	3.1
B2	Highlight L* = 85	65.9	3.7	84.8	84.9	2.6	1.4	0.9	4.4
C2	Highlight L* = 75	70.3	3.3	77.1	77.1	2.9	1.9	2.1	5.2
D2	Midtone L* = 63	74.9	2.9	69.5	69.5	2.8	2.0	2.2	5.0
E2	Midtone L* = 50	80.4	2.4	60.8	60.8	2.8	2.2	2.8	5.0
F2	Midtone L* = 38	84.8	2.0	52.1	51.8	2.6	2.1	2.8	4.6
A3	Highlight L* = 82	67.0	3.6	82.5	82.6	2.7	1.6	1.3	4.7
B3	Midtone L* = 72	71.7	3.2	74.8	74.7	2.9	2.0	2.2	5.2
C3	Midtone L* = 60	75.8	2.8	67.6	67.5	2.9	2.1	2.3	5.0
D3	Midtone L* = 47	81.5	2.3	59.0	58.9	2.8	2.2	2.9	5.0
E3	Midtone L* = 35	85.5	1.9	50.5	50.4	2.5	2.1	2.6	4.5
F3	Shadow L* = 25	89.3	1.6	41.5	41.1	2.2	1.8	2.2	3.7
A4	Midtone L* = 69	72.1	3.2	72.8	72.8	2.9	2.0	2.0	5.0
B4	Midtone L* = 57	77.2	2.7	65.5	65.4	2.9	2.1	2.5	5.1
C4	Midtone L* = 45	82.0	2.2	57.3	57.1	2.7	2.2	2.8	4.9
D4	Midtone L* = 32	86.5	1.8	48.2	48.0	2.4	2.0	2.5	4.2
E4	Shadow L* = 20	91.4	1.4	37.1	36.7	2.0	1.7	2.0	3.3
F4	Shadow L* = 10	97.5	0.8	23.5	23.2	1.1	0.9	0.6	1.3
A5	Midtone L* = 55	77.6	2.6	64.0	63.8	2.9	2.2	2.5	5.1
B5	Midtone L* = 41	83.7	2.1	54.6	54.5	2.7	2.2	2.8	4.8
C5	Shadow L* = 29	88.5	1.6	44.9	44.7	2.4	2.0	2.5	4.1
D5	Shadow L* = 15	94.3	1.1	30.3	30.0	1.6	1.4	1.5	2.5
E5	Shadow L* = 5	98.3	0.7	20.6	20.5	0.8	0.7	0.4	1.0
F5	Max Black	100.0	0.4	15.8	15.9	0.4	0.4	0.6	1.0
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		78.8	98.3	2.5					
Average Score for the Worst 10% (3 lowest scoring patches)		60.1	96.0	4.3					

78.2_{color} / 98.1_{tone}



Original Print Colors
(measured before light exposure)



Colors after 80 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*

80 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	59.4	4.4	97.6	97.8	1.6	0.1	-3.3	0.8
B1	Highlight L* = 96	59.8	4.3	94.2	94.4	2.0	0.5	-2.0	2.0
C1	Highlight L* = 89	62.6	4.1	88.0	88.4	2.5	1.1	0.0	3.8
D1	Highlight L* = 78	70.3	3.3	79.5	79.8	2.8	1.8	2.1	5.2
E1	Midtone L* = 66	73.5	3.0	71.0	71.1	2.9	2.0	2.2	5.1
F1	Midtone L* = 52	78.6	2.5	61.8	61.8	2.9	2.2	2.7	5.2
A2	Highlight L* = 92	60.1	4.3	90.5	90.7	2.3	0.9	-0.9	3.2
B2	Highlight L* = 85	65.4	3.8	84.8	85.0	2.6	1.4	0.9	4.5
C2	Highlight L* = 75	69.7	3.4	77.1	77.2	2.9	1.9	2.1	5.3
D2	Midtone L* = 63	74.2	2.9	69.5	69.5	2.8	2.1	2.2	5.0
E2	Midtone L* = 50	79.6	2.4	60.8	60.8	2.8	2.2	2.8	5.1
F2	Midtone L* = 38	84.1	2.0	52.1	51.8	2.6	2.2	2.8	4.7
A3	Highlight L* = 82	66.1	3.7	82.5	82.8	2.7	1.6	1.3	4.8
B3	Midtone L* = 72	71.0	3.3	74.8	74.9	2.9	2.0	2.2	5.3
C3	Midtone L* = 60	75.0	2.9	67.6	67.6	2.9	2.1	2.3	5.1
D3	Midtone L* = 47	80.5	2.4	59.0	58.9	2.8	2.2	2.9	5.1
E3	Midtone L* = 35	84.6	2.0	50.5	50.3	2.5	2.1	2.6	4.6
F3	Shadow L* = 25	88.8	1.6	41.5	41.0	2.2	1.9	2.2	3.8
A4	Midtone L* = 69	71.3	3.2	72.8	72.9	2.9	2.0	2.0	5.1
B4	Midtone L* = 57	76.6	2.7	65.5	65.4	2.9	2.1	2.5	5.1
C4	Midtone L* = 45	81.3	2.3	57.3	57.2	2.7	2.2	2.8	5.0
D4	Midtone L* = 32	85.9	1.9	48.2	47.9	2.4	2.0	2.5	4.3
E4	Shadow L* = 20	91.2	1.4	37.1	36.6	2.0	1.7	2.0	3.3
F4	Shadow L* = 10	97.2	0.8	23.5	23.3	1.1	0.9	0.6	1.4
A5	Midtone L* = 55	76.5	2.7	64.0	63.8	2.9	2.2	2.5	5.2
B5	Midtone L* = 41	82.9	2.1	54.6	54.5	2.7	2.2	2.8	4.9
C5	Shadow L* = 29	87.7	1.7	44.9	44.6	2.4	2.0	2.5	4.2
D5	Shadow L* = 15	93.8	1.2	30.3	29.9	1.6	1.4	1.5	2.5
E5	Shadow L* = 5	98.7	0.6	20.6	20.6	0.8	0.7	0.4	1.0
F5	Max Black	100.0	0.4	15.8	16.1	0.4	0.5	0.6	0.9

Summary Results

I*Color

I*tone

ΔE

Average Score for all patches

78.2

98.1


2.6

**Average Score for the Worst 10%
(3 lowest scoring patches)**

59.8


96.7

4.3




AARDENBURG IMAGING
& ARCHIVES

77.6_{color} / 97.9_{tone}



Original Print Colors
(measured before light exposure)





Colors after 90 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*

90 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	59.0	4.4	97.6	97.8	1.6	0.1	-3.3	0.9
B1	Highlight L* = 96	59.4	4.4	94.2	94.4	2.0	0.5	-2.0	2.1
C1	Highlight L* = 89	62.1	4.1	88.0	88.4	2.5	1.1	0.0	3.9
D1	Highlight L* = 78	69.7	3.4	79.5	79.8	2.8	1.8	2.1	5.3
E1	Midtone L* = 66	72.8	3.1	71.0	71.1	2.9	2.1	2.2	5.1
F1	Midtone L* = 52	77.9	2.6	61.8	61.8	2.9	2.2	2.7	5.2
A2	Highlight L* = 92	59.7	4.3	90.5	90.8	2.3	0.9	-0.9	3.2
B2	Highlight L* = 85	64.9	3.8	84.8	85.1	2.6	1.4	0.9	4.6
C2	Highlight L* = 75	69.0	3.5	77.1	77.3	2.9	1.9	2.1	5.4
D2	Midtone L* = 63	73.6	3.0	69.5	69.5	2.8	2.1	2.2	5.1
E2	Midtone L* = 50	78.9	2.5	60.8	60.8	2.8	2.2	2.8	5.2
F2	Midtone L* = 38	83.3	2.1	52.1	51.7	2.6	2.2	2.8	4.8
A3	Highlight L* = 82	65.5	3.8	82.5	82.8	2.7	1.6	1.3	4.9
B3	Midtone L* = 72	70.5	3.3	74.8	74.9	2.9	2.0	2.2	5.3
C3	Midtone L* = 60	74.3	2.9	67.6	67.5	2.9	2.1	2.3	5.2
D3	Midtone L* = 47	79.8	2.4	59.0	58.9	2.8	2.3	2.9	5.2
E3	Midtone L* = 35	84.0	2.0	50.5	50.2	2.5	2.1	2.6	4.6
F3	Shadow L* = 25	88.4	1.7	41.5	40.9	2.2	1.9	2.2	3.8
A4	Midtone L* = 69	70.7	3.3	72.8	72.9	2.9	2.0	2.0	5.2
B4	Midtone L* = 57	75.8	2.8	65.5	65.4	2.9	2.2	2.5	5.2
C4	Midtone L* = 45	80.5	2.4	57.3	57.2	2.7	2.2	2.8	5.1
D4	Midtone L* = 32	85.2	1.9	48.2	47.8	2.4	2.0	2.5	4.4
E4	Shadow L* = 20	90.5	1.5	37.1	36.5	2.0	1.7	2.0	3.4
F4	Shadow L* = 10	96.9	0.9	23.5	23.1	1.1	0.9	0.6	1.4
A5	Midtone L* = 55	76.0	2.8	64.0	63.9	2.9	2.2	2.5	5.2
B5	Midtone L* = 41	82.1	2.2	54.6	54.4	2.7	2.2	2.8	5.0
C5	Shadow L* = 29	87.1	1.8	44.9	44.4	2.4	2.0	2.5	4.2
D5	Shadow L* = 15	93.2	1.3	30.3	29.7	1.6	1.4	1.5	2.6
E5	Shadow L* = 5	98.2	0.8	20.6	20.2	0.8	0.7	0.4	1.0
F5	Max Black	100.0	0.3	15.8	15.8	0.4	0.5	0.6	1.0
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		77.6	97.9	2.6					
Average Score for the Worst 10% (3 lowest scoring patches)		59.4	97.0	4.4					

78.1_{color} / 98.2_{tone}




*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


100 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	58.9	4.4	97.6	97.7	1.6	0.1	-3.3	0.9
B1	Highlight L* = 96	59.5	4.3	94.2	94.3	2.0	0.5	-2.0	2.1
C1	Highlight L* = 89	62.1	4.1	88.0	88.3	2.5	1.1	0.0	3.8
D1	Highlight L* = 78	70.3	3.3	79.5	79.8	2.8	1.8	2.1	5.3
E1	Midtone L* = 66	73.2	3.0	71.0	71.1	2.9	2.0	2.2	5.1
F1	Midtone L* = 52	78.6	2.5	61.8	61.8	2.9	2.2	2.7	5.2
A2	Highlight L* = 92	59.2	4.4	90.5	90.7	2.3	0.9	-0.9	3.3
B2	Highlight L* = 85	65.0	3.8	84.8	85.0	2.6	1.4	0.9	4.5
C2	Highlight L* = 75	69.6	3.4	77.1	77.2	2.9	1.9	2.1	5.3
D2	Midtone L* = 63	74.1	3.0	69.5	69.5	2.8	2.1	2.2	5.1
E2	Midtone L* = 50	79.6	2.4	60.8	60.8	2.8	2.2	2.8	5.1
F2	Midtone L* = 38	83.9	2.0	52.1	51.9	2.6	2.2	2.8	4.7
A3	Highlight L* = 82	66.0	3.7	82.5	82.7	2.7	1.6	1.3	4.8
B3	Midtone L* = 72	70.8	3.3	74.8	74.8	2.9	2.0	2.2	5.3
C3	Midtone L* = 60	75.1	2.9	67.6	67.5	2.9	2.1	2.3	5.1
D3	Midtone L* = 47	80.5	2.4	59.0	58.9	2.8	2.2	2.9	5.1
E3	Midtone L* = 35	84.8	2.0	50.5	50.3	2.5	2.1	2.6	4.5
F3	Shadow L* = 25	89.0	1.6	41.5	41.0	2.2	1.8	2.2	3.7
A4	Midtone L* = 69	71.0	3.3	72.8	72.9	2.9	2.0	2.0	5.2
B4	Midtone L* = 57	76.3	2.8	65.5	65.4	2.9	2.2	2.5	5.2
C4	Midtone L* = 45	81.1	2.3	57.3	57.2	2.7	2.2	2.8	5.0
D4	Midtone L* = 32	85.9	1.9	48.2	47.9	2.4	2.0	2.5	4.3
E4	Shadow L* = 20	91.1	1.4	37.1	36.6	2.0	1.7	2.0	3.3
F4	Shadow L* = 10	97.1	0.9	23.5	23.2	1.1	0.9	0.6	1.4
A5	Midtone L* = 55	76.4	2.7	64.0	63.8	2.9	2.2	2.5	5.2
B5	Midtone L* = 41	82.9	2.1	54.6	54.5	2.7	2.2	2.8	4.9
C5	Shadow L* = 29	87.9	1.7	44.9	44.6	2.4	2.0	2.5	4.1
D5	Shadow L* = 15	94.0	1.1	30.3	30.0	1.6	1.4	1.5	2.5
E5	Shadow L* = 5	98.4	0.7	20.6	20.5	0.8	0.7	0.4	1.0
F5	Max Black	100.0	0.5	15.8	16.1	0.4	0.5	0.6	1.0
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		78.1	98.2	2.6					
Average Score for the Worst 10% (3 lowest scoring patches)		59.2	96.8	4.4					

78.3_{color}/98.2_{tone}



Original Print Colors
(measured before light exposure)




Colors after 120 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*


120 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	59.9	4.3	97.6	97.8	1.6	0.1	-3.3	0.8
B1	Highlight L* = 96	60.1	4.3	94.2	94.4	2.0	0.5	-2.0	2.0
C1	Highlight L* = 89	62.7	4.1	88.0	88.4	2.5	1.1	0.0	3.8
D1	Highlight L* = 78	70.4	3.3	79.5	79.8	2.8	1.8	2.1	5.2
E1	Midtone L* = 66	73.6	3.0	71.0	71.2	2.9	2.0	2.2	5.0
F1	Midtone L* = 52	78.7	2.5	61.8	61.9	2.9	2.2	2.7	5.1
A2	Highlight L* = 92	60.6	4.3	90.5	90.8	2.3	0.9	-0.9	3.1
B2	Highlight L* = 85	65.7	3.8	84.8	85.2	2.6	1.4	0.9	4.5
C2	Highlight L* = 75	69.9	3.4	77.1	77.3	2.9	1.9	2.1	5.3
D2	Midtone L* = 63	74.4	2.9	69.5	69.5	2.8	2.1	2.2	5.0
E2	Midtone L* = 50	79.4	2.5	60.8	60.8	2.8	2.2	2.8	5.2
F2	Midtone L* = 38	84.1	2.0	52.1	51.9	2.6	2.2	2.8	4.7
A3	Highlight L* = 82	66.2	3.7	82.5	82.9	2.7	1.6	1.3	4.8
B3	Midtone L* = 72	71.2	3.2	74.8	75.0	2.9	2.0	2.2	5.3
C3	Midtone L* = 60	75.2	2.9	67.6	67.6	2.9	2.1	2.3	5.1
D3	Midtone L* = 47	80.7	2.3	59.0	59.0	2.8	2.2	2.9	5.1
E3	Midtone L* = 35	84.7	2.0	50.5	50.3	2.5	2.1	2.6	4.5
F3	Shadow L* = 25	89.0	1.6	41.5	41.1	2.2	1.8	2.2	3.7
A4	Midtone L* = 69	71.5	3.2	72.8	72.9	2.9	2.0	2.0	5.1
B4	Midtone L* = 57	76.4	2.7	65.5	65.5	2.9	2.2	2.5	5.2
C4	Midtone L* = 45	81.3	2.3	57.3	57.2	2.7	2.2	2.8	5.0
D4	Midtone L* = 32	86.1	1.8	48.2	47.9	2.4	2.0	2.5	4.3
E4	Shadow L* = 20	91.0	1.4	37.1	36.6	2.0	1.7	2.0	3.3
F4	Shadow L* = 10	97.2	0.8	23.5	23.2	1.1	0.9	0.6	1.4
A5	Midtone L* = 55	76.9	2.7	64.0	63.9	2.9	2.2	2.5	5.1
B5	Midtone L* = 41	83.1	2.1	54.6	54.5	2.7	2.2	2.8	4.9
C5	Shadow L* = 29	87.9	1.7	44.9	44.6	2.4	2.0	2.5	4.1
D5	Shadow L* = 15	93.9	1.1	30.3	30.0	1.6	1.4	1.5	2.5
E5	Shadow L* = 5	98.5	0.7	20.6	20.4	0.8	0.7	0.4	1.0
F5	Max Black	100.0	0.3	15.8	15.9	0.4	0.5	0.6	0.9
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		78.3	98.2	2.6					
Average Score for the Worst 10% (3 lowest scoring patches)		60.2	97.3	4.3					

78.3_{color}/98.3_{tone}



Original Print Colors
(measured before light exposure)




Colors after 140 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*

140 Mlux-hrs Light Exposure (i.e., after) Compared to Original Print Colors (i.e., before)

Column/row	Color Patch	I*Color	ΔE	L*		a*		b*	
				Before	After	Before	After	Before	After
A1	Media White	58.5	4.4	97.6	97.8	1.6	0.1	-3.3	0.9
B1	Highlight L* = 96	59.1	4.4	94.2	94.4	2.0	0.5	-2.0	2.1
C1	Highlight L* = 89	62.1	4.1	88.0	88.5	2.5	1.1	0.0	3.8
D1	Highlight L* = 78	70.1	3.4	79.5	79.9	2.8	1.8	2.1	5.3
E1	Midtone L* = 66	73.7	3.0	71.0	71.3	2.9	2.0	2.2	5.0
F1	Midtone L* = 52	78.9	2.5	61.8	62.0	2.9	2.2	2.7	5.1
A2	Highlight L* = 92	59.2	4.4	90.5	90.8	2.3	0.9	-0.9	3.3
B2	Highlight L* = 85	65.1	3.8	84.8	85.2	2.6	1.4	0.9	4.5
C2	Highlight L* = 75	69.6	3.4	77.1	77.4	2.9	1.9	2.1	5.3
D2	Midtone L* = 63	74.5	2.9	69.5	69.6	2.8	2.1	2.2	5.0
E2	Midtone L* = 50	79.9	2.4	60.8	60.9	2.8	2.2	2.8	5.1
F2	Midtone L* = 38	84.6	2.0	52.1	52.0	2.6	2.1	2.8	4.7
A3	Highlight L* = 82	65.9	3.8	82.5	82.9	2.7	1.6	1.3	4.8
B3	Midtone L* = 72	71.1	3.3	74.8	75.0	2.9	2.0	2.2	5.3
C3	Midtone L* = 60	75.4	2.8	67.6	67.7	2.9	2.1	2.3	5.0
D3	Midtone L* = 47	80.9	2.3	59.0	59.1	2.8	2.2	2.9	5.1
E3	Midtone L* = 35	85.3	1.9	50.5	50.5	2.5	2.1	2.6	4.5
F3	Shadow L* = 25	89.3	1.5	41.5	41.2	2.2	1.8	2.2	3.7
A4	Midtone L* = 69	71.6	3.2	72.8	73.0	2.9	2.0	2.0	5.1
B4	Midtone L* = 57	76.7	2.7	65.5	65.6	2.9	2.2	2.5	5.1
C4	Midtone L* = 45	81.6	2.2	57.3	57.3	2.7	2.2	2.8	5.0
D4	Midtone L* = 32	86.3	1.8	48.2	48.0	2.4	2.0	2.5	4.2
E4	Shadow L* = 20	91.6	1.3	37.1	36.7	2.0	1.7	2.0	3.2
F4	Shadow L* = 10	97.4	0.8	23.5	23.4	1.1	0.9	0.6	1.3
A5	Midtone L* = 55	77.0	2.7	64.0	64.0	2.9	2.2	2.5	5.1
B5	Midtone L* = 41	83.4	2.1	54.6	54.7	2.7	2.2	2.8	4.8
C5	Shadow L* = 29	88.1	1.6	44.9	44.8	2.4	2.0	2.5	4.1
D5	Shadow L* = 15	94.2	1.1	30.3	30.1	1.6	1.4	1.5	2.5
E5	Shadow L* = 5	98.9	0.6	20.6	20.5	0.8	0.7	0.4	1.0
F5	Max Black	100.0	0.3	15.8	15.9	0.4	0.5	0.6	0.9
Summary Results		I*Color	I*tone	ΔE	 AARDENBURG IMAGING & ARCHIVES				
Average Score for all patches		78.3	98.3	2.6					
Average Score for the Worst 10% (3 lowest scoring patches)		58.9	97.4	4.4					



Original Print Colors
(measured before light exposure)



Next update is for 160 Megalux-hours
light exposure

*Epson Stylus Pro 7000, Cone Piezography Carbon Sepia K6,
PremierArt™ Alise Bright White*



AARDENBURG IMAGING
& ARCHIVES